

January 30, 2004

## SEALANT COMPATIBILITY WITH EPDM AND CCW-705 TWF

Carlisle does not endorse or recommend any particular sealants for through wall applications. However, we have tested some common construction sealants for compatibility with our products. Below is a chart showing our results. This is based on testing under laboratory conditions. A field test is advised to determine suitability under actual use conditions.

Sealant Trade Name*	Performance with EPDM	Performance with 705 TWF
Sonneborn NPI	Unacceptable	Excellent
NPC SolarSeal 900	Acceptable	Good
Vulkem 116 (Mameco)	Unacceptable	Very Good
Dymonic Polyurethane (Tremco)	Unacceptable	Acceptable
Carlisle PT-304	Unacceptable	Very Good
Clippership Roof Cement	Unacceptable	Unacceptable
Silaflex Ia	Unacceptable	Very Good
Silpruf Weatherproofing Sealant (GE)	Unacceptable	Acceptable
Silpruf LM (GE)	Not tested	Acceptable using GE 3195 primer
Pecora 895	Marginally Acceptable	Very Good
Pecora 863	Unacceptable	Unacceptable
Pecora 890	Acceptable	Very Good
Dow Corning 790	Excellent	Very Good
Dow Corning 791	Unacceptable	Very Good

\* Priming might be required by the sealant manufacturer.

For your convenience, a copy of this and other Technical Bulletins, can be found on our website at [www.carlisle-ccw.com](http://www.carlisle-ccw.com) under "Technical Bulletins" in the Training & Reference Library Section.