

#XJ15 Double-J Control Joint (XJ15)

Expanded flange control joint with a taped reveal for a clean finish

#XJ15 Expanded Flange Control Joint (Double-J) is used to relieve stresses in large plastered areas of walls, ceilings, and stucco areas. This expanded wing control joint minimizes cracking and assures proper plaster and stucco thickness. The Double-J has a 5/16" reveal and rolled outer edges to prevent visible separation cracking. The applied plastic tape keeps the reveal clean and is removed easily after the finish application.

The #XJ15 enables plaster to key into the return lip to eliminate shrinkage separation, a preferred finish feature. The joint is taped, preventing stucco from getting caught inside during installation and providing a neatly finished job upon completion.

The #XJ15 Double-J Control Joint is also available in zinc alloy for increased corrosion resistance.

Product Data & Ordering Information:

Material: 26 Gauge, G60 Hot-Dipped Galvanized Steel
Also available in 99.97% pure Zinc - ASTM B69 compliant

Dimensions: 1/2" to 7/8" grounds, 10' lengths

Ground	Length	Pcs./Ctn.	Ft./Ctn.	Wt./Ctn.	Ctn./Skid
1/2"	10'	24	240	54 lbs.	27
3/4"	10'	24	240	69 lbs.	30
7/8"	10'	24	240	76 lbs.	30

Code Approvals & Performance Standards

- [ASTM A653](#) Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process
- [ASTM C1063](#) Standard Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster
- [ASTM C1861](#) Standard Specification for Lathing and Furring Accessories, and Fasteners, for Interior and Exterior Portland Cement-Based Plaster
- [SDS For ASTM A653 Steel Finishing Products](#) For Interior Finishing and Exterior Finishing

Storage:

All stored materials shall be kept dry. Materials shall be stacked off the ground, supported on a level platform, and protected from the weather and surface contamination conforming to ASTM C1063.

Limitations:

Galvanized steel products should not be used with magnesium oxychloride cement stucco or Portland cement stucco containing calcium chloride additives. The selection of the appropriate type of material for accessories shall be determined by the surrounding climatic and environmental conditions such as salt air, industrial pollution and high humidity.

Sustainability Credits For more details and LEED letters contact Technical Services at 888-437-3244 or visit clarkdietrich.com/LEED.

- **LEED v4.1 MR Credit:** Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- **LEED v4 MR Credit:** Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

