

**350S200-33-P (33ksi, CP60, Punched)**
**3-1/2" structural stud with S200 (2") flange - 33mils (20ga)**
**Coating:** CP60 per AISI S240

**Color Code:** White

**Geometric Properties**
**Web depth:** 3.500 in

**Thickness:** 33mils (20ga)

**Yield strength,  $F_y$ :** 33 ksi

**Flange width:** 2.000 in

**Design Thickness:** 0.0346 in

**\* $F_y$  with Cold-Work,  $F_{ya}$ :** 33.0 ksi

**Stiffening lip:** 0.625 in

**Min. steel thickness:** 0.0329 in

**Ultimate,  $F_u$ :** 45.0 ksi

**Gross Section Properties of Full Section, Strong Axis**

Cross sectional area (A)	0.292 in <sup>2</sup>
Member weight per foot of length	0.99 lb/ft
Moment of inertia (Ix)	0.599 in <sup>4</sup>
Section Modulus (Sx)	0.342 in <sup>3</sup>
Radius of gyration (Rx)	1.431 in
Gross moment of inertia (Iy)	0.175 in <sup>4</sup>
Gross radius of gyration (Ry)	0.773 in

**Effective Section Properties, Strong Axis**

Effective Area (Ae)	0.188 in <sup>2</sup>
Moment of inertia for deflection (Ix)	0.593 in <sup>4</sup>
Section modulus (Sx)	0.283 in <sup>3</sup>
Allowable bending moment (Ma)	5.59 in-k
Allowable moment based on distortion buckling (Mad)	5.76 in-k
Allowable shear force in web (solid section)	1024 lb
Allowable shear force in web (perforated section)	487 lb
Unbraced length (Lu)	53.7 in

**Torsional Properties**

St. Venant torsional constant (J x 1000)	0.117 in <sup>4</sup>
Warping constant (Cw)	0.541 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-1.760 in
Distance between shear center and web centerline (m)	1.037 in
Radii of gyration (Ro)	2.396 in
Torsional flexural constant (Beta)	0.461

- Effective properties incorporate the strength increase from the cold work of forming.
- Gross properties are based on the cross section away from the punchouts.
- Effective properties are based on knockout/punched sections.

**Code Approvals & Performance Standards**

- [AISI S100-16 \(2020\) w/S2-20](#) North American Specification for the Design of Cold-Formed Steel Structural Members
- [AISI S240-20](#) North American Standard for Cold-Formed Steel Structural Framing
  - (Compliant to ASTM C955, but IBC replaced with AISI S200 in IBC 2015, AISI S240 in IBC 2018)
  - Section A3 Material - Chemical & mechanical requirements (Referencing ASTM A1003/A1003M)
  - Section A4 Corrosion Protection (Referencing ASTM A653/A653M)
  - Section C Installation - (Referencing ASTM C1007)
- [AISI S202-20](#) Code of Standard Practice for Cold-Formed Steel Structural Framing
  - Section F3 Delivery, Handling and Storage of Materials
- [IBC 2021](#) International Building Code
- [ICC-ES ESR-1166P](#) Structural Studs and Track
  - [ESR-1166P LABC and LARC](#) Supplement
  - [ESR-1166P Catalog](#) ClarkDietrich Structural Technical Design Guide (6/22/20)
- [Intertek CRRR-0206](#) Structural Studs and Track
- [SFIA Stud](#) Code Compliance Certification Program
- [SDS For ASTM A1003 Steel Framing Products](#) For Interior Framing, Exterior Framing and Clips/Accessories


**Structural Punchout**
**East Coast / Central punch spacing:**

Center of punchouts are 12" from lead end, then 24" o.c.

**West Coast punch spacing:**

Center of punchouts are 24" from lead end, then 24" o.c.

Center of tail end punchout not less than 12" from end of stud.

If lateral bracing is required for head-of-wall deflection track and a punchout is not spaced 12" from the top of stud, use strapping and blocking in lieu of CRC or Spazzer Bar lateral bridging.

If custom punchout patterns are required, contact ClarkDietrich Sales or local plant for requests.

**Sustainability Credits** For more details and LEED letters contact Technical Services at 888-437-3244 or visit [clarkdietrich.com/LEED](http://clarkdietrich.com/LEED).

- **LEED v4.1 MR Credit:** Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- **LEED v4 MR Credit:** Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).