


Technical Services: 888-437-3244, Engineering Services: 877-832-3206, Sales 800-543-7140

05.40.00 (Cold-Formed Metal Framing)

350T250-68 (50k 350 (3-1/2") structura	t <mark>si, CP60)</mark> I track with T250 (2-1/2'') leg - 6	8mils (14ga)	
Coating: CP60 per AISI	P60 per AISI S240 Color Code: Orange		
Geometric Properties			
Web depth: 3.750 in Leg width: 2.50 in	Thickness: 68mils (14ga) Design Thickness: 0.0713 in Min. steel thickness: 0.0677 in	Yield strength, Fy: 50 ksi *Fy with Cold-Work, Fya: 50.0 ks Ultimate, Fu: 65.0 ksi	
Gross Section Properties of Full Section, Strong Axis			
Cross sectional area (A)		0.605 in ²	
Member weight per foot of length		2.06 lb/ft	
Moment of inertia (Ix)		1.454 in ⁴	
Section Modulus (Sx)		0.776in ³	
Radius of gyration (Rx)		1.550 in	
Gross moment of inerita	(ly)	0.401 in ⁴	
Gross radius of gyration	(Ry)	0.814 in	
Effective Section Properties, Strong Axis			
Effective Area (Ae)		0.355 in ²	
Moment of inertia for deflection (lx)		1.168 in ⁴	
Section modulus (Sx)		0.479 in ³	
Allowable bending moment (Ma)		14.35 in-k	
Allowable shear force in	web	4536 lb	
	Torsional Propert	ies	
St. Venant torsional constant (J x 1000)		1.025 in ⁴	
Warping constant (Cw)		0.961 in ⁶	
Distance from shear center to neutral axis (Xo)		-1.703 in	



• Load-bearing walls

- Curtain walls
- Tall interior walls
- · Floor & ceiling joists
- Trusses



Sustainability Credits For more details and LEED letters contact Technical Services at 888-437-3244 or visit clarkdietrich.com/LEED.

- LEED v4.1 MR Credit: Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- LEED v4 MR Credit: Building Product Disclosure and Optimization: EPD (1 point) -Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) -Innovation Credit (up to 2 points).

Effective properties incorporate the strength increase from the cold work of forming.

Code Approvals & Performance Standards

Distance between shear center and web centerline (m)

Radii of gyration (Ro)

Torsional flexural constant (Beta)

- AISI S100-16 (2020) w/S2-20 North American Specification for the Design of Cold-Formed Steel Structural Members
- AISI S240-20 North American Standard for Cold-Formed Steel Structural Framing
- (Compliant to ASTM C955, but IBC replaced with AISI S200 in IBC 2015, AISI S240 in IBC 2018)

0.987 in

2.443 in

0.514

- Section A3 Material Chemical & mechanical requirements (Referencing ASTM A1003/A1003M)
- Section A4 Corrosion Protection (Referencing ASTM A653/A653M)
- · Section A5 Products Thickness, shapes, tolerances, identification
- Section C Installation (Referencing ASTM C1007)
- AISI S202-20 Code of Standard Practice for Cold-Formed Steel Structural Framing
 Section F3 Delivery, Handling and Storage of Materials
- SDS For ASTM A1003 Steel Framing Products For Interior Framing, Exterior Framing and Clips/Accessories