



# EUCALASTIC 1SL

## SINGLE-COMPONENT, SELF-LEVELING POLYURETHANE HYBRID SEALANT

### PACKAGING

30 oz (887 mL) cartridge, 12 per case  
Code: 174C 96 (Gray)  
Code: 174B 94 (Limestone)  
5 gallon (18.9 L) pail  
Code: 174C 05 (Gray, MTO)  
Code: 174B 05 (Limestone, MTO)

### APPROXIMATE YIELD

One cartridge yields 54 in<sup>3</sup> (884 cm<sup>3</sup>), and will cover 72 linear feet (22 m) in a 1/4" x 1/4" (6 mm x 6 mm) joint.  
One gallon (3.78 L) yields 231 in<sup>3</sup> (3,785 cm<sup>3</sup>).

### CLEAN UP

Tools, equipment and general clean-up can be done with EUCO SOLVENT or xylene before the material dries. Removal of dried EUCALASTIC 1SL can only be done by mechanical means.

### SHELF LIFE

1 year in original, unopened container

### SPECIFICATIONS AND COMPLIANCES

- ASTM C920, Type S, Grade P, Class 50, Use T, M, A, O, and I (Class 2)
- CAN/CGSB 19.13-M87, MC-1-25-B-N

### DESCRIPTION

EUCALASTIC 1SL is a single-component, low-modulus, moisture-cure, self-leveling, polyurethane joint sealant. EUCALASTIC 1SL is formulated to be extremely durable in dynamic joints. It provides superior wear resistance to rubber tires and pedestrians in high traffic areas.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Skins rapidly and is tack-free in 7 to 8 hours @ 75 °F (24 °C)
- Remains adhesively and cohesively bonded during temperature cyclic movement
- Service temperature range: -40 °F to 185 °F (-40 to 85 °C)
- Extraordinary movement capability of +100% / -50%
- Ease of application; dispense and walk away, up to a 6% slope
- Jet Fuel Resistant \*Refer to jet fuel resistance bulletin

#### PRIMARY APPLICATIONS

- Concrete control & expansion joints
- Sidewalks
- Truck terminals
- Plazas
- Swimming pool decks
- Traffic loop sealant
- Interior and exterior applications

#### APPEARANCE

EUCALASTIC 1SL is a single-component sealant available in the colors Gray and Limestone. Gray is MTO in 5 gallon (18.9 L) pails.

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C639	Rheology	Grade P (Self-Leveling) will hold up to 6% slope
ASTM C661	Hardness Shore A	43-47
ASTM C719	Movement Capability	+100% / -50%
-	Skin Time	1.5 to 2 hours
ASTM C679	Tack-Free Time	7 to 8 hours
ASTM D412	Tensile Strength	250 psi (1.7 MPa)
ASTM D412	Elongation	600%
ASTM D412	Tear Strength	35 Pli (61.3 N/cm)
ASTM C794	Adhesion to Concrete	Dry: 31 Pli (54.3 N/cm) Submersed: 28 Pli (49.0 N/cm) Green: >15 Pli (>26.3 N/cm) Saturated (SSD): >15 Pli (>26.3 N/cm)
ASTM C510	Stain & Color Change	No stain/No color change
ASTM C793	Effects of Accelerated Aging	No Cracking or chalking

---

## DIRECTIONS FOR USE

**Joint Dimensions:** Joint width should be 4 times the expected joint movement, but not less than 1/4" (6 mm). Width to depth ratios should be equal for joints that are 1/4" (6 mm) to 1/2" (13 mm) in width. If joint width is 1/2" (13 mm) to 1" (25 mm), the depth of EUCOLASTIC 1SL should be 1/2 the width, with 1/2" (13 mm) being the maximum allowable depth of EUCOLASTIC 1SL. Use backer rod or bond breaker tape to limit the depth of application and to prevent three-sided adhesion.

**Applications of EUCOLASTIC 1SL that are deeper than what is recommended can cause bubbling or incomplete curing of the material.**

**Surface Preparation:** EUCOLASTIC 1SL can be installed in new concrete 24 hours after forms are stripped. The concrete can be damp during application, but do not apply sealant where there is standing water in or nearby the joints. Excess standing water will cause bubbling of the sealant. The joints must be clean and sound. All curing & sealing compounds, oil, dirt, debris, paint, form release agents and any other foreign material must be removed. The final step in cleaning should be the complete removal of all residue by solvent wiping the joint.

**Priming:** EUCOLASTIC 1SL typically bonds to common construction materials without a primer. However, due to the variance in surface textures of some non-porous materials (metal, glass, certain stones, etc.), a field adhesion test is recommended on these materials to verify adhesion or the need for a primer. The field adhesion test for joint sealants is described in ASTM C1193. EUCOLASTIC PRIMER is required to prime the joint facing when the sealant will be in service under water after application and curing. See Eucolastic Primer technical data sheet for use instructions.

**Mixing:** EUCOLASTIC 1SL is a single-component sealant and requires no pre-blending. It should be used directly from the cartridge.

**Placement:** Ensure that all the necessary preparation work is completed. Place backer rod or bond breaker tape into the joints and make sure they are secured in place. Using standard caulking guns, dispense the sealant directly from the cartridge into the joint. Once the joint is full, leave it alone and allow it to self level to a nice and smooth finish. EUCOLASTIC 1SL will hold a slope up to 6%.

**Curing:** EUCOLASTIC 1SL requires no special curing. The moisture in the air and substrate will cure the sealant. A skin forms on the surface in about 1.5 to 2 hours at 72 °F (22 °C) and 50% relative humidity. It will be tack-free in 7 to 8 hours. EUCOLASTIC 1SL cures at rate of about 1/16" (1.6 mm) per day. The cure time will increase or decrease as temperatures and humidity levels fluctuate.

---

## PRECAUTIONS/LIMITATIONS

- The surface temperature of the substrate must be at least 40 °F (4 °C) and rising, but below 150 °F (66 °C), at the time of application.
- Do not use Eucolastic (1NS or 1SL) in submerged applications in swimming pools.
- For best results, store sealant at room temperature prior to application.
- Contact surfaces must be clean and dry.
- Do not use underneath a polyurethane deck coating unless the sealant has fully cured.
- In all cases, consult the Safety Data Sheet before use.

Rev. 06.23

---

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.