



# SURFLEX

## NON-METALLIC FLOOR HARDENER

### PACKAGING

50 lb (22.7 kg) bag  
 Code: 066 50 (natural)  
 Code: 166§ 50 (colors, some MTO)

### APPROXIMATE COVERAGE

SURFLEX may be applied at rates from 0.5 to 2.0 lb/ft<sup>2</sup> (2.4 to 9.8 kg/m<sup>2</sup>). Greater application rates yield better total abrasion resistance, and may be used with special considerations. Contact your Euclid Chemical Company representative for recommended procedures.

### CLEAN UP

Clean tools and equipment with water before the material hardens.

### SHELF LIFE

2 years in original, unopened package

### SPECIFICATIONS AND COMPLIANCES

- Canadian Food Inspection Agency compliant

### DESCRIPTION

SURFLEX is a quartz-silica mixture of finely graded non-metallic aggregates, plasticizer and cement binder. It is an economical concrete floor hardener recommended for both interior and exterior use. It is particularly valuable because of its non-rusting characteristics when floors will be frequently wet. SURFLEX is available in several colors.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Hardens concrete in one economical operation
- Use of hard and properly graded aggregates increases the wear resistance over plain concrete floors
- Ready-to-use factory blend eliminates messy and expensive job mixing and minimizes errors
- Non-rusting materials make it possible to use SURFLEX outdoors as well as indoors

#### PRIMARY APPLICATIONS

- Lobbies and waiting rooms of commercial and public buildings
- Corridors and washrooms in institutional and public buildings
- Auto showrooms and service centers
- Factory and warehouse floors
- Commercial and industrial facilities
- Restaurants and dairies

#### APPEARANCE

SURFLEX is a free flowing powder as packaged. Standard colors are Natural (cement-colored), Light Gray, and Light Reflective. SURFLEX is also available made-to-order in Battleship Gray, Brown, Diamond Green, French Gray, Tan, Terra Cotta, and Tile Red. The final finish can be any texture normally achieved with concrete and should be specified by the owner. In addition, the joints of a SURFLEX floor can be filled with a matching color available in EUCO QWIKJOINT UVR polyurea joint filler.

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	2 in. (50 mm) cubes, mixed at 5.25 lb (2.38 kg) of water per 50 lb (22.7 kg) bag 7 days . . . . .10,000 psi (69.0 MPa) 28 days . . . . .12,000 psi (82.8 MPa)
ASTM C779	Relative Abrasion Resistance	Abrasion @ 30 min.      Abrasion @ 60 min 7 days . . . . . 0.019" (0.48 mm). . . . . 0.042" (1.07 mm) 28 days. . . . . 0.013" (0.33 mm). . . . . 0.036" (0.91 mm)

---

## DIRECTIONS FOR USE

The contractor and engineer are encouraged to consult and review the Euclid Chemical bulletin **“Dry Shake Floor Hardeners - Application Instructions”**. The document offers instructions detailing the general installation of Euclid Chemical manufactured dry shake floor hardeners. **Note:** *If the contractor is not familiar with the standard application techniques of a dry shake floor hardener, a pre-job meeting is suggested to review the project concrete mix design as well as placement and curing details unique to the particular job. Contact your local Euclid Chemical Company representative for additional information.*

**Concrete Mix Design Note:** Air content must be below 3% for all dry shakes. Cement should be the only cementitious material present in the mix. The use of supplementary cementitious materials, such as fly ash, slag, and microsilica can cause delayed bleeding and are not recommended for use with a dry shake hardener.

**Application Tips:** Colored (pigmented) dry shakes require special attention for a uniform color. If the job involves placement of SURFLEX, care should be taken with regards to the following; delay application of the shake as long as possible to get the maximum color saturation at the surface of the slab, apply the shake as evenly as possible and in two applications for maximum uniformity. For color consistency, do not over trowel the floor.

**Curing and Sealing:** After finishing operations are complete and the surface will not be marred by foot traffic, apply a Euclid Chemical curing compound or cure and seal according to product instructions. To produce an exceptionally durable and dustproof surface, cure with a dissipating curing compound such as KUREZ DR VOX, then densify with EUCO DIAMOND HARD.

---

## PRECAUTIONS/LIMITATIONS

- The use of supplementary cementitious materials are not recommended for use with a dry shake hardener.
- Proper curing and sealing is required.
- Do not cure this product with UltraSil 7 or UltraSil DC9
- Sufficient manpower is required to produce consistent results on large placements.
- **Important:** Air-entraining admixtures may complicate finishing operations and cause blistering. Contact The Euclid Chemical Company if application of this product will be over air entrained concrete with more than 3% total air content.
- For additional abrasion resistance beyond that offered by SURFLEX, consider the use of EUCO-PLATE HD, an iron aggregate floor hardener.
- Store product in a dry place.
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- In all cases, consult the Safety Data Sheet before use.

Rev. 06.24

---

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.