



SURFLEX TR

NON-METALLIC, TRAP ROCK FLOOR HARDENER

PACKAGING

55 lb (24.9 kg) bag
Code: 166TR 55

APPROXIMATE COVERAGE

SURFLEX TR may be applied at rates from 0.75 to 2.0 lb/ft² (3.7 to 9.8 kg/m²). The higher the application rate the better total abrasion resistance. Greater application rates may be used with special considerations. Contact your Euclid Chemical Company representative for recommended procedures.

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

2 years in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- Canadian Food Inspection Agency compliant

DESCRIPTION

SURFLEX TR is a special formulation of finely graded trap rock aggregates, plasticizers and a cement binder. It is an economical concrete floor hardener recommended for both interior and exterior use. SURFLEX TR has been designed to give increased abrasion resistance to both interior and exterior floors and slabs.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Use of hard and properly graded aggregates increases the wear resistance over plain concrete floors
- Ready-to-use factory blend eliminates messy and expensive job mixing and minimizes errors
- Non-rusting materials make it possible to use SURFLEX TR outdoors as well as indoors

PRIMARY APPLICATIONS

- Loading docks
- High wear floors and aiseways
- Factory and warehouse floors
- Commercial and industrial facilities
- Restaurants and dairies

APPEARANCE

SURFLEX TR is a free flowing powder as packaged. It is available in a natural cement color only. The final troweled appearance can be any texture consistent with that expected from concrete and should be specified by the owner.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength	2 in. (50 mm) cubes, mixed at 5.13 lb (2.32 kg) of water per 50 lb (22.7 kg) bag 7 days10,000 psi (69.0 MPa) 28 days13,000 psi (89.7 MPa)
ASTM C779	Relative Abrasion Resistance	Abrasion @ 30 min. Abrasion @ 60 min 7 days 0.013" (0.33 mm). 0.035" (0.89 mm) 28 days. 0.008" (0.20 mm). 0.032" (0.81 mm)

DIRECTIONS FOR USE

The contractor and engineer are encouraged to consult and review the Euclid Chemical bulletin **“Dry Shake Floor Hardeners - Application Instructions”**. The document offers instructions detailing the general installation of Euclid Chemical manufactured dry shake floor hardeners. **Note:** *If the contractor is not familiar with the standard application techniques of a dry shake floor hardener, a pre-job meeting is suggested to review the project concrete mix design as well as placement and curing details unique to the particular job. Contact your local Euclid Chemical Company representative for additional information.*

Concrete Mix Design Note: Air content must be below 3% for all dry shakes. Cement should be the only cementitious material present in the mix. The use of supplementary cementitious materials, such as fly ash, slag, and microsilica can cause delayed bleeding and are not recommended for use with a dry shake hardener.

Curing and Sealing: After finishing operations are complete and the surface will not be marred by foot traffic, apply a Euclid Chemical curing compound, cure and seal, or water cure according to product instructions. To produce an exceptionally durable and dustproof surface, cure with a dissipating curing compound such as KUREZ DR VOX, then densify with EUCO DIAMOND HARD.

PRECAUTIONS/LIMITATIONS

- The use of supplementary cementitious materials are not recommended for use with a dry shake hardener.
- Do not cure this product with UltraSil 7 or UltraSil DC9
- Interior concrete must be non air-entrained. For exterior, air-entrained concrete, contact The Euclid Chemical Company for special instructions.
- For additional abrasion resistance beyond that offered by SURFLEX TR consider the use of EUCO-PLATE HD, an iron aggregate floor hardener.
- Store in a dry place.
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- In all cases, consult the Safety Data Sheet before use.

Rev. 02.24

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.