



# EverGuard®

SINGLE-PLY ROOFING SYSTEMS

## Bonding Adhesive

### Description

EverGuard® WB181 Bonding Adhesive is a water-based acrylic emulsion copolymer-based adhesive useful for bonding both TPO smooth and fleece-back and PVC fleece-back roofing membranes to various substrates.

- Suitable for roofing and flashing membranes, including fleece-back membranes
- Compatible with polyiso and fiber board, insulations, and fiberglass-faced gypsum panels
- Compatible with concrete, masonry, metal, and wood flashing substrates

### Application

Mating surfaces should be dry, clean, and free from oil, grease, and other contaminants.

Stir the adhesive thoroughly before use, either manually or by means of powered mixing equipment.

Apply adhesive evenly, avoiding puddles. Do not apply adhesive in lap areas, as this will prevent proper heat-welding. Using a standard solvent-resistant roller, apply the adhesive at the following coverage rates:

### SR-Type Smooth Reinforced Membrane

Approximately one gallon per 115–125 sq. ft. (3.79 L/10.68–11.61 sq. m) of surface area—approximately 600 sq. ft. (55.74 sq. m) of bonded area per pail. Apply to both the underside of the membrane and the substrate surface. *Install membrane once adhesive has dried and turned clear.*



## WB181 Bonding Adhesive

### FB-Type Fleece-Back Membrane

Approximately one gallon per 115–125 sq. ft. (3.79 L/10.68–11.61 sq. m) of surface area—approximately 600 sq. ft. (55.74 sq. m) of bonded area per pail. Apply only to the substrate surface. *Install membrane immediately onto wet adhesive; do NOT allow adhesive to dry.* Roll membrane onto the substrate surface and broom the membrane to ensure close contact between the membrane and the substrate surface.

See published application and specifications manual for detailed instructions.

### Physical Properties

**Weight Per Gallon:** 8.6–9.0 lb. (3.9–4.1 kg/liter)

**Viscosity (Brookfield cps):** 14,000–18,000

**Solids Content %:** 60.0–65.0

**VOC:** <20 g/L

**Storage:** Keep from freezing; store above 40°F (4.4°C)

**Installation Temperature:** Minimum application temperature is 40°F (4.4°C) and rising

Quality You Can Trust...From North America's Largest Roofing Manufacturer!™

[gaf.com](http://gaf.com)