



UltraSpan™ US1100

Pre-Cured Silicone Weatherstrip

Product Description

UltraSpan US1100 is a low modulus pre-cured silicone rubber weatherstrip and is an excellent candidate to consider for use in new and remedial sealing, splicing, flashing, roofing applications, and oversealing of failed building sealants. UltraSpan can provide a long lasting, durable, watertight weatherseal as a primary or a secondary seal over moving and non-moving joints. UltraSpan can be applied in the field or factory and bonded to a wide variety of construction materials.

Key Features and Typical Benefits

- **Silicone Durability**—Pre-cured weatherstrip exhibits excellent long-term resistance to natural weathering, including: ultraviolet radiation, high and low temperatures, rain and snow, with negligible change in elasticity performance.
- **High Performance Rubber**—The Low Modulus (+200%) movement capability can reduce strain on substrate surfaces and can accommodate seismic movements, live loads, and absorb large amounts of elongation while providing excellent recovery from high movement construction joints.
- **Silicone Compatibility**—Compatible with all GE silicone sealants allowing UltraSpan to be adhered to a wide range of construction materials.
- **Product Versatility**—Achieve a complete warrantable weatherseal system when used in combination with GE SilShield™ SEC2400 Silicone Architectural Coating and GE SilPruf™ family of sealants.
- **Unique Ridged Profile**—Control sealant thickness and reduce squeeze-out for cleaner installation and improved application quality.
- **Product Offering**—Available in a variety of standard sizes from 1 to 5 inch widths in 100 ft. rolls. Available in custom colors and flat sheets, up to 48 inches in width.
- **Potential Reduced Labor Cost**—An economical alternative to cast-in-place wet-seals or cutting out and reinstalling existing failed building sealants.
- **Thermal Stability**—Remains elastic over a wide range of temperature differentials of common building systems or facades -55°F (-48°C) to 400°F (93°C).

Potential Applications

- UltraSpan may be suitable for use as a weatherproofing splice material for building repair and restoration of existing failed building sealants.
- UltraSpan may be suitable for use when repairing failed sealants in building joints, leaking skylights, flashing, parapets, window perimeter joints and on EIFS.
- UltraSpan may be suitable for use on internal curtainwall frames and high movement splice areas.

Packaging

UltraSpan is available in 100 foot rolls. Standard widths are: 1", 1.5", 2", 3", 4", and 5". Custom UltraSpan is available in flat sheets up to 48 inches. Minimums apply.

Colors

UltraSpan is available in 8 standard colors, translucent, and can be custom colored.

Grade	Color
US1101	Translucent
US1102	White
US1103	Black
US1104	Limestone
US1108	Light Grey
US1109	Aluminum
US1110	Dark Grey
US1120	Precast White
US1197	Bronze



Colors—continued

ULTRASPAN PRODUCT DESIGNATION BY WIDTH AND COLOR

Overall Width Code	Overall Width	Working Width	UltraSpan Color and Width Guide							
			White	Black	Limestone	Light Gray	Aluminum	Dark Gray	Precast White	Bronze
10	1 inch	0.4 inches	US1102-10	US1103-10	US1104-10	US1108-10	US1109-10	US1110-10	US1120-10	US1197-10
15	1.5 inches	0.5 inches	US1102-15	US1103-15	US1104-15	US1108-15	US1109-15	US1110-15	US1120-15	US1197-15
20	2 inches	1 inch	US1102-20	US1103-20	US1104-20	US1108-20	US1109-20	US1110-20	US1120-20	US1197-20
30	3 inches	2 inches	US1102-30	US1103-30	US1104-30	US1108-30	US1109-30	US1110-30	US1120-30	US1197-30
40	4 inches	3 inches	US1102-40	US1103-40	US1104-40	US1108-40	US1109-40	US1110-40	US1120-40	US1197-40
50	5 inches	4 inches	US1102-50	US1103-50	US1104-50	US1108-50	US1109-50	US1110-50	US1120-50	US1197-50

Typical Physical Properties

Typical property values of UltraSpan US1100 as supplied and installed are set forth in the tables below.

Typical Properties – Supplied

Property	Value ⁽¹⁾	Test Method
Consistency	Pre-cured silicone rubber	

Typical Properties – Cured

Property	Value ⁽¹⁾	Test Method
Hardness, Durometer (Type A Indentor)	35 +/- 5	ASTM D2240
Ultimate Tensile Strength	780 psi (5.38 MPa)	ASTM D412
Ultimate Elongation	550%	ASTM D412
Tear Strength, die B	126 ppi	ASTM D624
Tensile at 50% Elongation	73 psi (0.50 MPa)	Internal Test ⁽²⁾
Tensile at 100% Elongation	101 psi (0.69 MPa)	Internal Test ⁽²⁾
Joint Movement Capability	+200/-100%	ASTM C719
Service Temperature Range	-55°F (-48°C) to +400°F (98°C)	

(1) Typical properties are average data and are not to be used as or to develop specifications.

(2) Contact Technical Services for a description of the test method.

- Seat the UltraSpan into the sealant using hand pressure. As the UltraSpan is seated, the sealant should fill the channels, usually a small amount of adhesive squeezes out alongside the UltraSpan.
- Small adjustments to the placement of UltraSpan may be done at this time, but lifting the UltraSpan and re-seating should be avoided as removing and re-seating may require additional sealant.
- Use a small roller to apply sufficient pressure to the UltraSpan to bond the part into its final location.
- Tool excess sealant and if masking tape was used, remove masking tape immediately.
- If mitered or field cut corners are used, apply enough sealant under the corner joint so the squeeze-out fills the miter joint.
- Apply masking tape in areas of high visibility to ensure good aesthetics.
- Horizontal joints must be completed before application of vertical joints.

Installation

For surface preparation and cleaning procedures, refer to the technical data sheet of the sealant being used to apply UltraSpan.

Weatherstrip Application

A sealant may be applied to either the UltraSpan and/or the substrate surface.

Apply two appropriate sized beads of sealant in sufficient amount to fill the grooved areas on the UltraSpan. Typically, a 1/8" to 3/8" bead will be sufficient but rougher surfaces may require a larger amount.




Joint Designs and Dimensions

Joint Movement – All moving (dynamic) joints must not allow movement in excess of the performance properties of the UltraSpan US1100 pre-cured weatherstrip.

Joint Width – When using UltraSpan US1100, refer to the nominal working width data below. The nominal working width is the largest joint width which can be covered with UltraSpan US1100. Refer to Figure below.

Nominal Overall Width (inches)	Nominal Working Width (inches)
1	0.4
1.5	0.5
2	1
3	2
4	3
5	4



“WORKING WIDTH” is the largest joint width that can be covered.

Applicable Standards

UltraSpan US1100 meets or exceeds the requirements of the following specifications:

American Society for Testing & Materials International
ASTM C1518 Standard Specification for Precured Elastomeric Silicone Joint Sealants; Movement Class 200, Tear Class PT.

UltraSpan US1100 carries SWR Institute validation @ +200% movement with Partial / Knotty Tear (PT) characteristics.

Technical Services

Additional technical information and literature may be available. Contact Technical Services or a representative. Laboratory testing and application engineering are available upon request.

Limitations

UltraSpan is not recommended:

- For use underwater or in other applications where the product will be in continuous contact with water.
- For use in food contact applications.
- When painting of the cured weather strip is desired (unless GE SilShield™ SEC2400 Architectural Wall Coating is used).
- Where frequent abrasion or physical abuse is encountered in joints on or below grade.

Precautions

Some materials that bleed plasticizers or oils can cause a discoloration on the surface of silicone weatherstrip. When sealing to or over such substrates as: rubberized gaskets, bituminous-based materials, butyl or oil-based products, oily woods, tapes, etc. Compatibility testing is recommended prior to use to confirm the suitability of these materials when in contact with each other.

Availability

Information on ordering US1100 and/or custom shapes can be obtained from Momentive Performance Materials, Waterford, NY or an authorized GE construction sealants product distributor. For information regarding cost or for available project warranty information, contact your local distributor or Momentive Performance Materials Territory Manager. Contact Customer Service at: 877-943-7325.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.siliconeforbuilding.com or, upon request, from any MPM representative. Use of other materials in conjunction with MPM sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.



Customer Service Centers

For additional information, please contact our Customer Service Team

AMERICAS	+1 800 295 2392 Toll Free* +1 704 805 6946 Direct Number Email: commercial.services@momentive.com
LATIN AMERICA	BRAZIL +55 11 4534 9650 Direct Number MEXICO +52 55 2169 7670 Direct Number *All American countries
EMEA – EUROPE, MIDDLE EAST, AFRICA & INDIA	EUROPE +390510924300 Direct Number INDIA, MIDDLE EAST & AFRICA +91 44 71212207 Direct Number* *All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka Email: 4information.eu@momentive.com
ASIA PACIFIC	CHINA 800 820 0202 Toll Free +86 21 3860 4892 Direct Number JAPAN +81 3 5544 3111 Direct Number KOREA +82 2 6201 4600 Direct Number SOUTH EAST ASIA, AUSTRALIA & NEW ZEALAND +60 3 9206 1543 Direct Number* *All East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region) Email: 4information.ap@momentive.com
Visit us at www.siliconeforbuilding.com	

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Before purchasing or using any Momentive products, please visit www.siliconeforbuilding.com/legaldisclaimer to view our full product and sales disclaimer. GE is a registered trademark of General Electric Company and is used under license by Momentive Performance Materials Inc. The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Copyright 2012-2023 Momentive Performance Materials Inc. All rights reserved.

www.siliconeforbuilding.com