

Marino\WARE® Product Submittal Data

PRODUCT NAME: 800QFH300-68


MARINO\WARE PART # 800QFH30068



PROPERTIES:

A. Web (in)	8	Yield Strength Fy (KSI)	50
B. Flange (in)	3	Tensile Strength Fu (KSI)	65
C. Lip (in)	1	Design Thickness (in)	0.0713
Mils	68	Minimum Thickness (in)	0.0677
Available Finish	G60, G90	Gauge	14

05.40.00 Cold-Formed Metal Framing



SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	1.10
Weight of Member: (lb/ft)	3.75
Moment of Inertia: Ix (in ⁴)	10.9
Section Modulus: Sx (in ³)	2.73
Radius of Gyration: Rx (in)	3.15
Moment of Inertia: Iy (in ⁴)	1.41
Section Modulus: Sy (in ³)	0.682
Radius of Gyration: Ry (in)	1.13

EFFECTIVE SECTION PROPERTIES - Unpunched

Moment of Inertia-Deflection: Ixe (in ⁴)	10.9
Section Modulus: Sxe (in ³)	2.52
Allowable Bending Moment: Malx (in-k)	75.4
Allowable Bending Moment: Madx (in-k)	65.7
Moment of Inertia: Iye (in ⁴)	1.41
Section Modulus: Sye (in ³)	0.662
Allowable Bending Moment: Maly (in-k)	19.8
Allowable Bending Moment: Mady (in-k)	18.5
Allowable shear: Vag (k)	4.220

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: Jx1000 (in ⁴)	1.87
Torsional Warping Constant: Cw (in ⁶)	19.8
Shear Center to Centroid on Principal X-axis: Xo (in)	-2.31
Radius of Gyration on the Centroid Principal axis: Ro (in)	4.08
Torsional Flexural Constant: β = [1-(xo/Ro) ²]	0.677

CODES & STANDARDS

- AISI S100 & S240
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021

GREEN INFO

- LEED credits available
- Contact Technical Services for more information



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 8/02/2024
©Copyright 2024 by Ware Industries, Inc. All rights reserved