

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600S300-97

MARINO\WARE PART # 600SX12

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	6"	Yield Strength Fy (KSI)	50
B. Flange (in)	3"	Tensile Strength Fu (KSI)	65
C. Lip (in)	5/8"	Design Thickness (in)	0.1017
Mils	97	Minimum Thickness (in)	0.0966
Available Finish	G60	Gauge	12

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	1.3469
Weight of Member: (lb/ft)	4.5833
Moment of Inertia: Ix (in ⁴)	7.7468
Section Modulus: Sx (in ³)	2.5823
Radius of Gyration: Rx (in)	2.3982
Gross Moment of Inertia: Iy (in ⁴)	1.7414
Gross Radius of Gyration: Ry (in)	2.3982

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	7.7468
Section Modulus: Sxe (in ³)	2.5078
Allowable Bending Moment: Ma (in-k)	82.864
Allowable strong axis shear away from punch: Vag (lb)	10472
Allowable strong axis shear at punch: Vanet (lb)	3805

TORSIONAL SECTION PROPERTIES



St. Venant Torsional Constant: Jx1000 (in ⁴)	4.6437
Torsional Warping Constant: Cw (in ⁶)	15.2434
Shear Center to Centroid on Principal X-axis: Xo (in)	-2.516
Shear Center to Mid-Plane of the Web: m (in)	1.504
Radius of Gyration on the Centroid Principal axis: Ro (in)	3.657
Torsional Flexural Constant: β [1-(xo/Ro) ²]	0.527

CODES & STANDARDS

- AISI S100-12 & ICC ES ESR-4062
- Framing meets ASTM A 1003, A 653, & C 955
- Meets IBC 2015 & 2012, FBC 2014, CSSA code compliant

GREEN INFO

- LEED v3 & LEED v4 credits available
- Contact Technical Services for more information.



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 1/5/2017
©Copyright 2017 by Ware Industries, Inc. All rights reserved