

Marino\WARE® Product Submittal Data

PRODUCT NAME: 1200S200-54

MARINO\WARE PART # 120SJ16

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	12"	Yield Strength Fy (KSI)	50
B. Flange (in)	2"	Tensile Strength Fu (KSI)	65
C. Lip (in)	5/8"	Design Thickness (in)	0.0566
Mils	54	Minimum Thickness (in)	0.0538
Available Finish	G60	Gauge	16

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.953
Weight of Member: (lb/ft)	3.241
Moment of Inertia: Ix (in ⁴)	17.668
Section Modulus: Sx (in ³)	2.945
Radius of Gyration: Rx (in)	4.307
Gross Moment of Inertia: Iy (in ⁴)	0.394
Gross Radius of Gyration: Ry (in)	0.643

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	16.104
Section Modulus: Sxe (in ³)	2.073
Allowable Local Bending Moment: Mal (in-k)	62.06
Allowable Distortional Bending Moment: Mad (in-k)	53.10
Allowable strong axis shear away from punch: Vag (lb)	1377
Allowable strong axis shear at punch: Vanet (lb)	1377

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: Jx1000 (in ⁴)	1.017
Torsional Warping Constant: Cw (in ⁶)	11.550
Shear Center to Centroid on Principal X-axis: Xo (in)	-1.302
Shear Center to Mid-Plane of the Web: m (in)	0.681
Radius of Gyration on the Centroid Principal axis: Ro (in)	4.475
Torsional Flexural Constant: β 1-(xo/Ro) ²	0.947



CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

Note: Web depth to thickness ratio (h/t) exceeds 200. Web stiffeners required at all support points and concentrated loads.



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 11/5/2023
©Copyright 2023 by Ware Industries, Inc. All rights reserved