

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600S162-54

MARINO\WARE PART # 600SS16

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	6"	Yield Strength Fy (KSI)	50
B. Flange (in)	1-5/8"	Tensile Strength Fu (KSI)	65
C. Lip (in)	1/2"	Design Thickness (in)	0.0566
Mils	54	Minimum Thickness (in)	0.0538
Available Finish	G60	Gauge	16

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.556
Weight of Member: (lb/ft)	1.89
Moment of Inertia: Ix (in ⁴)	2.860
Section Modulus: Sx (in ³)	0.953
Radius of Gyration: Rx (in)	2.267
Gross Moment of Inertia: Iy (in ⁴)	0.180
Gross Radius of Gyration: Ry (in)	0.570

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	2.86
Section Modulus: Sxe (in ³)	0.92
Allowable Local Bending Moment: Mal (in-k)	30.30*
Allowable Distortional Bending Moment: Mad (in-k)	23.00
Allowable strong axis shear away from punch: Vag (lb)	2823
Allowable strong axis shear at punch: Vanet (lb)	1947

* Allowable Bending Moment includes cold work of forming

TORSIONAL SECTION PROPERTIES



St. Venant Torsional Constant: Jx1000 (in ⁴)	0.594
Torsional Warping Constant: Cw (in ⁶)	1.337
Shear Center to Centroid on Principal X-axis: Xo (in)	-1.049
Shear Center to Mid-Plane of the Web: m (in)	0.663
Radius of Gyration on the Centroid Principal axis: Ro (in)	2.562
Torsional Flexural Constant: $\beta 1-(x_0/R_0)^2$	0.832

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 11/5/2023
©Copyright 2023 by Ware Industries, Inc. All rights reserved