

Marino\WARE® Product Submittal Data

PRODUCT NAME: 800S250-97

MARINO\WARE PART # 800SE12

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	8"	Yield Strength Fy (KSI)	50
B. Flange (in)	2-1/2"	Tensile Strength Fu (KSI)	65
C. Lip (in)	5/8"	Design Thickness (in)	0.1017
Mils	97	Minimum Thickness (in)	0.0966
Available Finish	G60	Gauge	12

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	1.37
Weight of Member: (lb/ft)	4.670
Moment of Inertia: Ix (in ⁴)	12.792
Section Modulus: Sx (in ³)	3.198
Radius of Gyration: Rx (in)	3.053
Gross Moment of Inertia: Iy (in ⁴)	1.009
Gross Radius of Gyration: Ry (in)	0.857

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	12.789
Section Modulus: Sxe (in ³)	3.053
Allowable Local Bending Moment: Mal (in-k)	103*
Allowable Distortional Bending Moment: Mad (in-k)	82.90
Allowable strong axis shear away from punch: Vag (lb)	10885
Allowable strong axis shear at punch: Vanet (lb)	5938

* Allowable Bending Moment includes cold work of forming

TORSIONAL SECTION PROPERTIES



St. Venant Torsional Constant: Jx1000 (in ⁴)	4.731
Torsional Warping Constant: Cw (in ⁶)	13.091
Shear Center to Centroid on Principal X-axis: Xo (in)	-1.607
Shear Center to Mid-Plane of the Web: m (in)	1.008
Radius of Gyration on the Centroid Principal axis: Ro (in)	3.555
Torsional Flexural Constant: β 1-(xo/Ro) ²	0.796

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 11/5/2023
© Copyright 2023 by Ware Industries, Inc. All rights reserved