

Marino\WARE® Product Submittal Data

PRODUCT NAME: 362S137-68

MARINO\WARE PART # 358SC14

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	3-5/8"	Yield Strength Fy (KSI)	50
B. Flange (in)	1-3/8"	Tensile Strength Fu (KSI)	65
C. Lip (in)	3/8"	Design Thickness (in)	0.0713"
Mils	68	Minimum Thickness (in)	0.0677"
Available Finish	G90	Gauge	14

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.470
Weight of Member: (lb/ft)	1.60
Moment of Inertia: Ix (in ⁴)	0.922
Section Modulus: Sx (in ³)	0.509
Radius of Gyration: Rx (in)	1.401
Gross Moment of Inertia: Iy (in ⁴)	0.109
Gross Radius of Gyration: Ry (in)	0.480

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: Ixe (in ⁴)	0.92
Section Modulus: Sxe (in ³)	0.49
Allowable Local Bending Moment: Mal (in-k)	14.77
Allowable Distortional Bending Moment: Mad (in-k)	15.2
Allowable strong axis shear away from punch: Vag (lb)	4370
Allowable strong axis shear at punch: Vanet (lb)	1004

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: Jx1000 (in ⁴)	0.797
Torsional Warping Constant: Cw (in ⁶)	0.302
Shear Center to Centroid on Principal X-axis: Xo (in)	-0.959
Shear Center to Mid-Plane of the Web: m (in)	0.592
Radius of Gyration on the Centroid Principal axis: Ro (in)	1.764
Torsional Flexural Constant: β 1-(xo/Ro) ²	0.704

CODES & STANDARDS

- AISI S100-12 & ICC ES ESR-4062
- Framing meets ASTM A 1003, A 653, & C 955
- Meets IBC 2015 & 2012, FBC 2014, CSSA code compliant

GREEN INFO

- LEED v3 & LEED v4 credits available
- Contact Technical Services for more information.

