

# Marino\WARE® Product Submittal Data

**PRODUCT NAME:** 400S137-54

**MARINO\WARE PART #** 400SC16

05.40.00 Cold-Formed Metal Framing

**PROPERTIES:**

<b>A. Web (in)</b>	4"	<b>Yield Strength Fy (KSI)</b>	50
<b>B. Flange (in)</b>	1-3/8"	<b>Tensile Strength Fu (KSI)</b>	65
<b>C. Lip (in)</b>	3/8"	<b>Design Thickness (in)</b>	0.0566
<b>Mils</b>	54	<b>Minimum Thickness (in)</b>	0.0538
<b>Available Finish</b>	G90	<b>Gauge</b>	16

**SECTION PROPERTIES**

**GROSS SECTION PROPERTIES**

Cross Sectional Area: <b>A</b> (in <sup>2</sup> )	0.401
Weight of Member: (lb/ft)	1.36
Moment of Inertia: <b>Ix</b> (in <sup>4</sup> )	0.953
Section Modulus: <b>Sx</b> (in <sup>3</sup> )	0.477
Radius of Gyration: <b>Rx</b> (in)	1.542
Gross Moment of Inertia: <b>Iy</b> (in <sup>4</sup> )	0.094
Gross Radius of Gyration: <b>Ry</b> (in)	0.484

**EFFECTIVE SECTION PROPERTIES**

Moment of Inertia-Deflection: <b>Ixe</b> (in <sup>4</sup> )	0.95
Section Modulus: <b>Sxe</b> (in <sup>3</sup> )	0.43
Allowable Local Bending Moment: <b>Mal</b> (in-k)	12.82
Allowable Distortional Bending Moment: <b>Mad</b> (in-k)	12.40
Allowable strong axis shear away from punch: <b>Vag</b> (lb)	3372
Allowable strong axis shear at punch: <b>Vanet</b> (lb)	1223

**TORSIONAL SECTION PROPERTIES**



St. Venant Torsional Constant: <b>Jx1000</b> (in <sup>4</sup> )	0.428
Torsional Warping Constant: <b>Cw</b> (in <sup>6</sup> )	0.311
Shear Center to Centroid on Principal X-axis: <b>Xo</b> (in)	-0.940
Shear Center to Mid-Plane of the Web: <b>m</b> (in)	0.583
Radius of Gyration on the Centroid Principal axis: <b>Ro</b> (in)	1.870
Torsional Flexural Constant: <b>β</b> 1-(xo/Ro) <sup>2</sup>	0.747

**CODES & STANDARDS**

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

**GREEN INFO**

- LEED credits available
- Contact Technical Services for more information.



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 11/5/2023  
©Copyright 2023 by Ware Industries, Inc. All rights reserved