

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600S250-43

MARINO\WARE PART # 600SE18

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	6"	Yield Strength Fy (KSI)	33
B. Flange (in)	2-1/2"	Tensile Strength Fu (KSI)	45
C. Lip (in)	5/8"	Design Thickness (in)	0.0451
Mils	43	Minimum Thickness (in)	0.0428
Available Finish	G90	Gauge	18

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.537
Weight of Member: (lb/ft)	1.828
Moment of Inertia: I_x (in ⁴)	3.083
Section Modulus: S_x (in ³)	1.028
Radius of Gyration: R_x (in)	2.396
Gross Moment of Inertia: I_y (in ⁴)	0.458
Gross Radius of Gyration: R_y (in)	0.923

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: I_{xe} (in ⁴)	3.062
Section Modulus: S_{xe} (in ³)	0.918
Allowable Local Bending Moment: M_{al} (in-k)	18.14
Allowable Distortional Bending Moment: M_{ad} (in-k)	15.70
Allowable strong axis shear away from punch: V_{ag} (lb)	1415
Allowable strong axis shear at punch: V_{anet} (lb)	1240

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: J_{x1000} (in ⁴)	0.364
Torsional Warping Constant: C_w (in ⁶)	3.411
Shear Center to Centroid on Principal X-axis: X_o (in)	-1.874
Shear Center to Mid-Plane of the Web: m (in)	1.136
Radius of Gyration on the Centroid Principal axis: R_o (in)	3.179
Torsional Flexural Constant: β 1-(x _o /R _o) ²	0.652

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

