

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600S300-118

MARINO\WARE PART # 600SX110

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	6"	Yield Strength Fy (KSI)	50
B. Flange (in)	3"	Tensile Strength Fu (KSI)	65
C. Lip (in)	5/8"	Design Thickness (in)	0.1242
Mils	118	Minimum Thickness (in)	0.1180
Available Finish	G90	Gauge	10

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	1.53
Weight of Member: (lb/ft)	5.209
Moment of Inertia: I_x (in ⁴)	8.787
Section Modulus: S_x (in ³)	2.929
Radius of Gyration: R_x (in)	2.396
Gross Moment of Inertia: I_y (in ⁴)	1.704
Gross Radius of Gyration: R_y (in)	1.055

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: I_{xe} (in ⁴)	8.785
Section Modulus: S_{xe} (in ³)	2.797
Allowable Local Bending Moment: M_{al} (in-k)	94.2*
Allowable Distortional Bending Moment: M_{ad} (in-k)	79.70
Allowable strong axis shear away from punch: V_{ag} (lb)	12526
Allowable strong axis shear at punch: V_{anet} (lb)	3622

* Allowable Bending Moment includes cold work of forming

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: J_{x1000} (in ⁴)	7.872
Torsional Warping Constant: C_w (in ⁶)	12.684
Shear Center to Centroid on Principal X-axis: X_o (in)	-2.212
Shear Center to Mid-Plane of the Web: m (in)	1.328
Radius of Gyration on the Centroid Principal axis: R_o (in)	3.427
Torsional Flexural Constant: β 1-(x _o /R _o) ²	0.583

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

