

# Marino\WARE® Product Submittal Data

**PRODUCT NAME:** 800S200-54

**MARINO\WARE PART #** 800SJ16

05.40.00 Cold-Formed Metal Framing

## PROPERTIES:

<b>A. Web (in)</b>	8"	<b>Yield Strength Fy (KSI)</b>	50
<b>B. Flange (in)</b>	2"	<b>Tensile Strength Fu (KSI)</b>	65
<b>C. Lip (in)</b>	5/8"	<b>Design Thickness (in)</b>	0.0566
<b>Mils</b>	54	<b>Minimum Thickness (in)</b>	0.0538
<b>Available Finish</b>	G90	<b>Gauge</b>	16

## SECTION PROPERTIES

### GROSS SECTION PROPERTIES

Cross Sectional Area: <b>A</b> (in <sup>2</sup> )	0.726
Weight of Member: (lb/ft)	2.471
Moment of Inertia: <b>I<sub>x</sub></b> (in <sup>4</sup> )	6.574
Section Modulus: <b>S<sub>x</sub></b> (in <sup>3</sup> )	1.644
Radius of Gyration: <b>R<sub>x</sub></b> (in)	3.009
Gross Moment of Inertia: <b>I<sub>y</sub></b> (in <sup>4</sup> )	0.357
Gross Radius of Gyration: <b>R<sub>y</sub></b> (in)	0.701

### EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: <b>I<sub>xe</sub></b> (in <sup>4</sup> )	6.572
Section Modulus: <b>S<sub>xe</sub></b> (in <sup>3</sup> )	1.499
Allowable Local Bending Moment: <b>M<sub>al</sub></b> (in-k)	44.88
Allowable Distortional Bending Moment: <b>M<sub>ad</sub></b> (in-k)	36.00
Allowable strong axis shear away from punch: <b>V<sub>ag</sub></b> (lb)	2091
Allowable strong axis shear at punch: <b>V<sub>anet</sub></b> (lb)	2091

### TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: <b>J<sub>x1000</sub></b> (in <sup>4</sup> )	0.775
Torsional Warping Constant: <b>C<sub>w</sub></b> (in <sup>6</sup> )	4.663
Shear Center to Centroid on Principal X-axis: <b>X<sub>o</sub></b> (in)	-1.265
Shear Center to Mid-Plane of the Web: <b>m</b> (in)	0.804
Radius of Gyration on the Centroid Principal axis: <b>R<sub>o</sub></b> (in)	3.338
Torsional Flexural Constant: <b>β 1-(x<sub>o</sub>/R<sub>o</sub>)<sup>2</sup></b>	0.856

## CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

## GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

