

Marino\WARE® Product Submittal Data

PRODUCT NAME: 250T125-68

MARINO\WARE PART # 212ST14

05.40.00 Cold-Formed Metal Framing

PROPERTIES:

A. Web (in)	2-1/2"	Yield Strength Fy (KSI)	50
B. Flange (in)	1-1/4"	Tensile Strength Fu (KSI)	65
Mils	68	Design Thickness (in)	0.0713
Available Finish	G60	Minimum Thickness (in)	0.0677
		Gauge	14

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Cross Sectional Area: A (in ²)	0.355
Weight of Member: (lb/ft)	1.21
Moment of Inertia: I_x (in ⁴)	0.408
Section Modulus: S_x (in ³)	0.297
Radius of Gyration: R_x (in)	1.072
Gross Moment of Inertia: I_y (in ⁴)	0.054
Gross Radius of Gyration: R_y (in)	0.389

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: I_x (in ⁴)	0.402
Section Modulus: S_x (in ³)	0.262
Allowable Bending Moment: M_a (in-k)	7.850
Allowable strong axis shear away from punch: V_{ag} (lb)	3199

TORSIONAL SECTION PROPERTIES

St. Venant Torsional Constant: J_{x1000} (in ⁴)	0.602
Torsional Warping Constant: C_w (in ⁶)	0.069
Shear Center to Centroid on Principal X-axis: X_o (in)	-0.740
Shear Center to Mid-Plane of the Web: m (in)	0.444
Radius of Gyration on the Centroid Principal axis: R_o (in)	1.360
Torsional Flexural Constant: β [1-(x _o /R _o) ²]	0.704

CODES & STANDARDS

- AISI S100, S240 & ICC ES ESR-4062
- ASTM A 1003, A 653, & C 955
- IBC 2012, 2015, 2018, 2021 & FBC 2020, 2023

GREEN INFO

- LEED credits available
- Contact Technical Services for more information.

