

Marino\WARE® Product Submittal Data

PRODUCT NAME: 600SR300-97

05.40.00 Cold-Formed Metal Framing

MARINO\WARE PART # 600RX12

PROPERTIES:

A. Web (in)	6"	Yield Strength F_y (KSI)	50
B. Flange (in)	3"	Tensile Strength F_u (KSI)	65
C. Lip (in)	0.625"	Design Thickness (in)	0.1017
Mils	97	Minimum Thickness (in)	0.0966
Available Finish	CP60, CP90	Gauge	12

SECTION PROPERTIES

GROSS SECTION PROPERTIES

Weight of Member: (lb/ft)	3.80
Cross Sectional Area: A (in ²)	1.02
Moment of Inertia: I_x (in ⁴)	7.27
Section Modulus: S_x (in ³)	2.42
Radius of Gyration: R_x (in)	2.67
Gross Moment of Inertia: I_y (in ⁴)	1.17
Gross Radius of Gyration: R_y (in)	1.07

EFFECTIVE SECTION PROPERTIES

Moment of Inertia-Deflection: I_{xed} (in ⁴)	7.14
Section Modulus: S_{xe} (in ³)	2.19
Allowable Bending Moment: Ma (in-k)	65.5
Allowable Shear Force: Va (K)	2.36

TORSIONAL SECTION PROPERTIES


St. Venant Torsional Constant: Jx1000 (in ⁴)	3.52
Torsional Warping Constant: C_w (in ⁶)	10.3
Distance From Shear Center To Centroid Principle x-axis x_o (in.)	-2.53
Distance From Shear Center to Mid-Plane of Web m (in.)	1.39
Radius of Gyration on the Centroid Principal axis: r_o (in.)	3.83
$1 - (x_o/r_o)^2 = \beta$	0.564
Critical Unbraced Length, lateral torsional buckling excluded L_u (in.)	55.4

CODES & STANDARDS

- Meets ASTM A 1003, A 653, C955 & AISI S240
- Coating meets ASTM C 955 / AISI S240
- Meets IBC 2021, 2018
- IAPMO ES ER-0781

GREEN INFO

- LEED v4 credits available
- Contact Technical Services for more information



Section	A (in)	B (in)	C
3-5/8"	7.0	3.5	1-3/4
4"	7.0	3.5	1-3/4
6"	8.1	4.0	2-7/8



For more information, please contact Marino\WARE Technical Services at 866-545-1545.

This technical information reflects the most current information available and supersedes any and all publications, effective 7/1/2021
©Copyright 2021 by Ware Industries, Inc. All rights reserved