

3	03 64 00	Injection Grouting
31	31 01 70	Maintenance of Tunneling and Mining
31	31 73 00	Tunnel Grouting

# MasterRoc<sup>®</sup> MP 325

## Solvent-free, low viscosity, hydrophilic grout for rock injection and consolidation of sand and silt strata

### Description

MasterRoc MP 325 grout is a “one-component” injection system, based on a nanometric colloidal silica suspension. The open time can be adjusted with a 10 percent solution of NaCl as accelerator. The gel time may be adjusted by varying the quantity of accelerator added to MasterRoc MP 325 grout Component A. Due to the hydrophilic nature of the product, it also adheres well to wet surfaces. There is no foam reaction that can negatively influence the bond. Equipment can easily be cleaned using water.

### Applications

MasterRoc MP 325 grout has been developed for consolidation of sand- and silt-based strata and for injection into fine joints and fissures in rock. These properties are particularly well-suited for the following:

- Slope stabilization in rock
- For ground improvement
- Pre-injection grouting for tunneling projects
- Waterproofing of existing tunnels
- Mining applications for waterproofing and stabilization

### Features

- Very low viscosity
- Workable between 40 °F and 105 °F (5 °C and 40 °C)
- Uses simple mixing and pumping equipment as used with cementitious grouts
- Can be used with both one- and two-component pumps

### Benefits

- Excellent penetration
- Controlled gel time with the use of a 10 percent solution of sodium chloride (NaCl) as accelerator
- Improved working safety, reduced environmental impact and low handling costs
- Non-aggressive
- Good bonding to wet surfaces
- Environmentally-preferable, contains no solvents nor toxic components

### Performance Characteristics

#### Technical Data

##### Typical values

##### MasterRoc MP 325 Grout Component A

Color	Clear
Viscosity*	~10 cP (mPa.s)
Density*	68.7 lb/ft <sup>3</sup> (1.098 kg/L)
pH*	10 ± 1
SiO <sub>2</sub> concentration	15 ± 1 %

\*at 68 °F (20 °C)



**Guidelines for Use**

Add a 10 percent solution of NaCl as accelerator to MasterRoc MP 325 grout Component A at the required ratio. Ensure Component A is continuously stirred during the addition of the accelerator, and fully mixed prior to pumping.

The fully mixed MasterRoc MP 325 grout is pumped with a one-component pump, such as a cement grout injection pump, through an injection packer system into the strata.

MasterRoc MP 325 grout Component A and the NaCl accelerator solution can also be injected via two-component equipment. If the product is used with two-component pumps, it is necessary to use a static “space” in-line mixer to get good mixing of MasterRoc MP 325 grout and the accelerator.

To achieve controlled, targeted injection into sands and gravels, the use of double packers with tube à manchette injection tubes (often referred to as “TAMs” or “SPPs”) with port centers is recommended, depending on the fineness of soils, and degree of stabilization required.

**Gel Time**

It is always important to do a pre-test to determine the appropriate dosage of accelerator prior to injection.

The gel time of MasterRoc MP 325 grout is controlled by the dosage of accelerator and is affected by temperature. The gel time can be adjusted between 10 minutes and up to several hours as indicated in Figure 1. For longer gel times, the temperature should also be considered.




Figure 1. Adjustable gel time with varying accelerator dosage. Values given are at 68 °F (20 °C).

**Cleaning of Injection Equipment**

All equipment can be cleaned with fresh water.

**Storage and Handling**

**Storage Temperature:** In unopened, tightly closed original containers, the components of MasterRoc MP 325 grout may be stored for up to 6 months, if stored in a dry area and within a temperature range of 40 °F and 95 °F (5 °C and 35 °C). Protect from sunlight. After 6 months, the product remains perfectly useable, but a modest increase in dosage of accelerator may be needed.

**Safety:** Colloidal silica will irritate the eyes and the skin. MasterRoc MP 325 grout contains no hazardous materials requiring labeling. However, standard precautions for handling chemical products should be observed: Avoid eye and skin contact and wear hand gloves and safety goggles. If contact occurs, rinse with plenty of water. In case of eye contact, seek medical advice. The cured MasterRoc MP 325 grout is physiologically harmless.

**Packaging**

MasterRoc MP 325 grout is available in standard sets containing:

- MasterRoc MP 325 Component A: 55 gal (208 L) drums or 264 gal (1,000 L) containers

**Related Documents**

Safety Data Sheets: MasterRoc MP 325 grout

**Additional Information**

For additional information about MasterRoc MP 325 grout, consult your local sales representative.

*Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in ~40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.*

## Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.