

PRODUCT DATA SHEET

Sika® Primer-176

(formerly MSeal P 176)

PRIMER FOR SIKAL SEALANTS

PRODUCT DESCRIPTION

Sika® Primer-176 is a high-solids, low-VOC solvent-based primer for priming joints and substrates before application of Sikaflex® NP 1, Sikaflex® TX 1, Sikaflex® NP 2 and Sikaflex® CR 195 sealants.

USES

- Interior or exterior
- Above grade
- As primers for Sika joint sealants

Substrates

- Concrete
- Masonry
- Metal

CHARACTERISTICS / ADVANTAGES

- High-solids, low VOCs, and easy to use
- Transparent and non-staining

PRODUCT INFORMATION

Chemical Base	Sika® Primer-176 is a solution of isocyanate adhesion promoters in an organic solvent.
Packaging	One pint (473 ml) cans Units are sold individually. Bulk shipments are available in cases of 12 units.
Shelf Life	2 years when properly stored
Storage Conditions	Store in unopened containers in a cool, dry area out of direct sunlight.
Color	Transparent (water white)
Flash Point	35-40°F(1.7 – 4°C)
Solid content by mass	59% by volume
Viscosity	90 cps

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

- Substrates such as copper, stainless, and galvanized steel typically require the use of a primer; Sika® Primer-173 or Sika® Primer-176 is acceptable. For Kynar 500-based coatings, use Sika® Primer-173 only. An adhesion test is recommended for any other questionable substrate.
- Be careful to apply Sika® Primer-173 only to joint faces; Sika® Primer-173 will darken upon UV exposure.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the job site.

SUBSTRATE PREPARATION

1. Masonry surfaces must be sound, clean, dry, and free of all paint, grease, oil, dirt, and foreign matter.
2. Concrete surfaces must be fully cured and free of laitance, moisture, or form oils.
3. Where necessary, clean joint surfaces by grinding, sandblasting or mechanical abrading; remove dust, dirt, and loose particles before priming.
4. Metal-edged joint surfaces must be clean and free of all rust, oil, and dirt.

APPLICATION

1. Apply Sika® Primer-176 to the cleaned joint surfaces by brushing on a thin, uniform coat. Use the primer as is; do not thin. Too much primer may act as a bond breaker.
2. Allow primer to dry for at least 30 minutes and up to 8 hours before applying sealant. Dry time will vary depending on temperature and humidity.
3. Sealant must be applied the same day as primer.

Drying Time

30 minutes to 8 hours, depending on temperature and humidity, (60 minutes at 72 °F [22 °C] and 50% relative humidity). Sika® Primer-176 will be tacky to the touch but will not transfer to the finger when dry.

CLEANING OF TOOLS

Brushes and tools may be cleaned with SikaSwell®-990 before the primer has dried. Dried primer must be removed by abrading.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet

Sika® Primer-176
September 2024, Version 02.01
02051600000002011

SikaPrimer-176-en-US-(09-2024)-2-1.pdf

