

# Product Data Sheet

## 300 RTS — Flexible Body Coat

### 871JB: Base 871J9 : Curing Agent 95UJB



<b>Description:</b>	300 RTS (Hempel 871JB) Flexible Body Coat is a 100% solids, elasticized methacrylate (MMA) resin.
<b>Recommended use:</b>	300 RTS is used as a body and/or base coat with Neogard RTS vehicular and pedestrian traffic systems. Example applications include: parking garages, stadiums, balconies, plaza decks, pedestrian walkways, rooftop recreational areas, and mechanical rooms. Can also be used under tile and pavers.
<b>Features:</b>	Remains flexible at low temperatures. Very fast turnaround from application to service. Can be applied at temperatures as low as 23°F/-5°C. Contact Neogard if applying below 30°F/-1°C. Must be mixed with Neogard RTS 600 BPO Initiator (see chart below). Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.
<b>Limitations:</b>	Do not apply to damp or contaminated surfaces. Not intended for use as a topcoat. Do not use with carbonate-based fillers.
<b>Availability:</b>	Available in North America. Not included in Group Assortment; other regions must confirm.

### Colors and packaging:

300 RTS (871J900000)	Amber (tintable)	5-gallon (4.5 gallon fill volume)
600 RTS (95UJB00000)	White	10-lb pail

### Physical constants:

Tensile strength:	615 psi	ASTM D638
Elongation:	204%	ASTM D638
Shore A:	91	ASTM D2240
Shore D:	41	ASTM D2240
Low-temperature crack bridging:	Pass at 40, 60, 80 mils	ASTM C1305
Permeance:	0.53 US/0.35 Metric Perms	ASTM D1653
MVT:	143.0mg m <sup>2</sup> 1 hour, 3.43g m <sup>2</sup> 24 hours	ASTM E96
Volume solids, mixed:	100%	Calculated
VOC:	<100 g/L	ASTM D5201
Shelf life:	12 months	

*The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

### Application details:

<b>Version, mixed product</b>	<b>871JB</b>
Mixing ratio:	Base 871J9 : Curing Agent 95UJB Ratio changes with temperature; see "600 RTS BPO initiator dosages" chart below
Thinning:	Coating is to be applied without thinning.
Application method:	Notched squeegee or gauge rake
Cleaning of tools:	Clean tools with Neogard 800 PMMA Cleaning Agent only. Other solvents may contaminate PMMA/PUMA coatings, and cause the coating to cure improperly. Neogard 800 PMMA is not for sale or use in the state of California and other areas with multi-purpose solvent VOC regulations. Please consult your Local, State and Federal air quality rules before use.
Mixing:	Jiffy Mixer preferred. Mix with 600 RTS for 30–45 seconds or until completely mixed. Note: Extended mixing time will shorten working time of the material.

# Product Data Sheet

300 RTS — Flexible Body Coat

871JB: Base 871J9 : Curing Agent 95UJB



<b>RTS 600 BPO initiator dosages:</b>	Temperature:	30°F/-1°C	35°F/2°C	40°F/4°C	45°F/7°C	50°F/10°C
	Fluid oz/Gallon:	12	11	10	9	8
	Temperature:	55°F/13°C	60°F/16°C	65°F/18°C	70°F/21°C	
	Fluid oz/Gallon:	7	6	5	4	
	Temperature:	75°F/24°C	80°F/27°C	85°F/29°C	90°F/32°C	
	Fluid oz/Gallon:	3.5	3	2.5	2	

**Safety:** Use with adequate ventilation. Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

**Surface preparation:** According to Neogard system Guide Specifications.

**Preceding coat:** According to Neogard system Guide Specifications.

**Subsequent coat:** According to Neogard system Guide Specifications.

**Storage:** Store at or below 77°F/25°C. Protect against direct sunlight. Contains paraffin, which may precipitate below 59°F/15°C.

**Note:** 300 RTS is for professional use only.

**Issued by:** Hempel (USA) – 871JB

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at [www.neogard.com](http://www.neogard.com) (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information )

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at [www.neogard.com](http://www.neogard.com). Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at [www.hempel.com](http://www.hempel.com). NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 300RTS-PDS ksk 10062021.docx

Neogard®, a part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - [www.neogard.com](http://www.neogard.com)