

Product Data Sheet

70750/70751 — Low-Modulus Epoxy
472JB: Base 472J9 : Curing Agent 95YJB



Description: 70750/70751 (Hempel 472JB) is a two-component, 100% solids, moisture tolerant, flexible, low-modulus epoxy.

Recommended use: As a binder for epoxy overlay systems and for use as a wearing course with aggregate for Neogard traffic bearing coating systems.

Note: Not for use as a topcoat (see Remarks on Page 2).

Features: Moisture tolerant.
Excellent viscosity for leveling.
Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70750 (472J900000)	Clear	15-gallon kit
70751 (95YJB00000)	Clear	

Physical constants:

Tensile strength	1,362 psi ± 100	ASTM D638
Elongation	81% ± 10	ASTM D638
Flexural strength	1,100 psi	ASTM D790
Taber abrasion	60 mg/1,000 CS-17	ASTM D4060
Shore D	65	ASTM D2240
Modulus of elasticity	42,000 psi	ASTM D790
Adhesion to concrete	960 psi	ASTM D4541
Water resistance	1.3% at 24 hours	ASTM D570
Viscosity	3,800–4,500 cps	ASTM D2196
Weight/gallon (mixed)	8.77 lbs/gal ± 0.25	ASTM D1475
Weight solids (mixed)	100%	ASTM D5201
Volume solids (mixed)	100%	ASTM D5201
VOC (mixed)	<100 g/L	ASTM D5201
Flash point		Refer to SDS
Shelf life	1 year	
Tack-free time at 73°F/22°C	4 hours	ASTM D5894

The above tested results are typical values. Individual lots may vary. Further technical information can be found at www.neogard.com.

Application details:

Version, mixed product

472JB
Base 472J9 : Curing Agent 95YJB
2 : 1 by volume; mix for 3–5 minutes before applying
Coating is to be applied without Thinning.
Accelerator: Not recommended
Roller/Rake/Squeegee/Notched squeegee
Application method: 30 minutes at 75°F/23°C
Pot life: Acetone or other VOC compliant multi-purpose solvents. Confirm compliance with Local, State and Federal air quality rules before use.
Cleaning of tools:

Safety: Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult Neogard Safety Data Sheets and follow all local or national safety regulations.

Surface preparation: According to Neogard Guide Specifications.

Product Data Sheet

70750/70751 — Low-Modulus Epoxy
472JB: Base 472J9 : Curing Agent 95YJB



Application conditions:	Ambient temperature must be between 40°F/4°C and 100°F/37°C, and a minimum of 5°F/3°C above dew point.
Preceding coat:	According to Neogard Guide Specifications.
Subsequent coat:	According to Neogard Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.
Remarks:	Not for use as a topcoat; product is too soft and will be damaged. Do not sand or roughen; product is too soft and will be damaged.

Note: **70750/70751 is for professional use only.**

Issued by: Hempel (USA) – 472JB

This Product Data Sheet (“PDS”) relates to the supplied product (“Product”) and is subject to update from time-to-time. Accordingly, the buyer/applicator should refer to the PDS current as of the time of delivery. In addition to the PDS, the buyer/applicator may receive some or all of the specifications, statements and/or guidelines listed below or available at www.neogard.com (the “Additional Documents”):

No.	Document Description
1	PDS
2	Guide Specification
3	Application Manual
4	Other Technical Support Information (i.e. summary application tables, troubleshooting guides, maintenance manuals, chemical resistance charts and other technical information)

In the event of a conflict between this PDS and the Additional Documents, the conflict shall be resolved in accordance with the order of priority set forth above. In addition, the buyer/applicator should refer to the relevant Safety Data Sheet current as of the time of delivery and available at www.neogard.com. Buyer/applicator is responsible for determining the suitability of the intended use of the Product, and Neogard disclaims all responsibility for any use, handling and storage of the Product that is not in accordance with the requirements set forth in the relevant PDS and the Additional Documents. The terms and provisions hereof apply to this PDS, the Additional Documents and any other documents supplied by Neogard in respect of the Product. The Product is supplied and all technical assistance is given subject to the General Conditions of Sale of Hempel Products and/or Services available at www.hempel.com. NEOGARD MAKES NO OTHER WARRANTY THAT EXTENDS BEYOND THE WARRANTY REFERENCED THEREIN INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTIES OR CONDITIONS OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NEOGARD WILL NOT BE LIABLE FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR BREACH OF ANY EXPRESS OR IMPLIED WARRANTY OR CONDITION, OR THAT IN ANY WAY ARISE IN RELATION TO THE PRODUCT. 70750-70751-PDS ksk 02212022.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com