



PROSOCO®

# Consolideck®

CONCRETE FLOORING PRODUCTS



# Blended Densifier

Consolideck® Blended Densifier is a blend of silicates designed specifically for steel-troweled or burnished concrete floors. This penetrating, economical treatment reacts with the concrete to quickly create a harder, denser surface.

Blended Densifier is safer and easier to apply than conventional sodium silicate hardeners.

## ADVANTAGES

- Unique formulation offers better performance than other densifiers when used on Type 1L cement mixes.
- Easy, one-step application. No scrubbing. No flushing. No caustic wastewater.
- Specifically designed for steel-troweled, power-troweled or burnished concrete finishes.
- Penetrates and reacts quickly to produce better initial and ultimate hardness.
- Provides better abrasion resistance than conventional hardeners.
- Can be burnished for a quick sheen.
- Suitable for use with wet or dry grinding and polishing procedures.
- Breathable and UV-stable. Will not yellow, discolor, peel or flake.
- VOC- Compliant. Non-flammable. Non-toxic. Low-odor.
- Cures quickly. Floors can be opened to traffic once dry.
- Treated surfaces are easier to maintain.
- May enhance or darken certain substrates.

## Limitations

- Will not prevent water penetration through structural cracks, defects or open joints.

## TYPICAL TECHNICAL DATA

<b>FORM</b>	Clear, colorless liquid
<b>SPECIFIC GRAVITY</b>	1.10
<b>pH</b>	11.5
<b>WT/GAL</b>	9.2 lbs
<b>ACTIVE CONTENT</b>	14%
<b>TOTAL SOLIDS</b>	14%
<b>VOC CONTENT</b>	0 g/L
<b>FREEZE POINT</b>	32° F (0° C)
<b>SHELF LIFE</b>	2 years in tightly sealed, unopened container

## REGULATORY COMPLIANCE

### VOC Compliance

Consolideck® Blended Densifier is compliant with the US Environmental Protection Agency's AIM VOC regulations.

Visit [www.prosoco.com/voccompliance](http://www.prosoco.com/voccompliance) to confirm compliance with individual district or state regulations.

## SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

**24-Hour Emergency Information:**  
**INFOTRAC at 800-535-5053**

# Product Data Sheet

## Consolideck® Blended Densifier

### PREPARATION

Protect people, vehicles, property, plants and all surfaces not designated to receive Blended Densifier from the product, splash and wind drift. Use polyethylene or other proven protective material.

Do not apply to surfaces which are frozen, dirty or have standing water. Surfaces must be clean, dry and absorbent. Confirm surface absorbency with a light water spray – surfaces designated for treatment should wet uniformly. If the surface does not wet uniformly, use the appropriate PROSOCO surface preparation cleaner or a mechanical process to remove remaining surface contaminants.

Blended Densifier is ideal for application to existing, cured concrete of any age. Surfaces must be clean and structurally sound. Remove all foreign materials including bond breakers, curing agents, surface grease and oil, and construction debris using the appropriate PROSOCO cleaners. Follow the appropriate cleaner with thorough water rinsing. Acid-stained concrete must be thoroughly neutralized and rinsed prior to application.

If the desired surface finish requires mechanical removal of the top layer of cement paste, best results are achieved by sanding or grinding the cured concrete surface to achieve a 50–200 grit finish before applying Blended Densifier. The increased surface density which Blended Densifier provides will make further sanding, grinding or diamond polishing proceed faster.

Application may begin as soon as prepared surfaces are dry.

### Surface and Air Temperatures

Temperatures for application should be 40–100° F (4–38° C).

### Equipment

Apply with low pressure sprayer or microfiber pad.

Spray applicators equipped with 0.5 gpm (gallon per minute) fan spray tip have proven effective for application of this product.

### Storage and Handling

Store in a cool, dry place. Always seal container after dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright

storage of factory-sealed containers in a dry place. Maintain temperatures of 40–100°F (4–38°C). Keep from freezing. Do not double stack pallets. Dispose of in accordance with local, state and federal regulations.

### APPLICATION

Read “Preparation” and the Safety Data Sheet before use.

**ALWAYS TEST** a small area of each surface to confirm suitability, coverage rate and desired results before beginning overall application. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let surface dry thoroughly before inspection.

### Dilution & Mixing

Do not dilute or alter. Use as supplied. Stir or mix well before use.

### Typical Coverage Rates

Variations in concrete quality, porosity, job site conditions, temperature and relative humidity will affect coverage rates and drying times.

Calculate the Target Coverage Rate by testing a representative section of the prepared surface using the published application instructions.

- 400–800 sq.ft. (37–74 sq.m.) per US gal

### Application Instructions

#### *Steel Troweled / Burnished Concrete*

1. Clean concrete of any dirt or residue.
2. Using a low pressure sprayer, apply a single saturating coat of Blended Densifier. Apply sufficient material to wet the surface without producing puddles. Use a Consolideck® microfiber pad to spread product evenly and ensure uniform wetting. To avoid overlap marks and streaks, always maintain a wet edge when applying and avoid spreading once drying begins.
3. Scrubbing is not necessary. Surface should remain wet for 10–15 minutes. Adjust rate of application accordingly. Allow treated surfaces to dry at least one hour.
4. Once dry, burnish with a high speed machine and diamond impregnated pad (800 grit) to remove residue and enhance the surface.



# Product Data Sheet

## Consolideck® Blended Densifier

*For increased hardening*, apply a second application of Blended Densifier and then burnish with a 1500 grit diamond impregnated pad once dry.

### Application Instructions

#### *Ground, Honed or Polished Concrete*

1. Sand, level or grind the concrete surface with a floor sander, orbital floor machine or diamond grinding as needed to achieve desired exposure. Grind floor to 200 grit resin bond diamonds.
2. Remove all dust and debris using a floor scrubbing machine and fresh water. Allow surfaces to dry.
3. Using a low pressure sprayer, apply a single saturating coat of Blended Densifier. Apply sufficient material to wet the surface without producing puddles. Use a clean Consolideck® microfiber pad to spread product evenly and ensure uniform wetting. To avoid overlap marks and streaks, always maintain a wet edge when applying and avoid spreading once drying begins.
4. Scrubbing is not necessary. Surface should remain wet for 10–15 minutes. Adjust application rate accordingly. Allow treated surfaces to dry at least one hour. Grind with 400 grit resins.

*For increased hardening*, apply a second light application of Blended Densifier. Allow to dry and continue polishing to desired level.

### Protective Treatment

*For additional shine and protection*, apply Consolideck® LSGuard® or PolishGuard.

*OR, for improved resistance to water or oily stains*, apply PROSOCO's Concrete Protector SB according to label instructions.

Call Customer Care at 800-255-4255 for assistance with proper product recommendation. Always obtain the Product Data for full limitations, application and safety information before applying any PROSOCO product.

### Cleanup

Before product dries, clean tools and equipment with fresh water. Immediately wash off over spray from glass, aluminum, polished or other surfaces with fresh water.

### Final Results

The floor is ready to use when dry. Surfaces exhibit reduced water absorption upon drying and maximum water resistance will develop over 7 days. Surface hardness and sheen often increase over time and with proper maintenance.

### Maintenance

Remove surface dust and debris daily using a microfiber pad or dry dust mop. Dry buff with a high-speed burnisher to refresh gloss.

Regular maintenance cleaning will improve surface shine. Maintain the floor with Consolideck® DailyKlean or LSKlean. For concrete floors regularly maintained with auto scrubbers, see Consolideck® DailyKlean ULTRA 15 or DailyKlean ULTRA 30 for easy dilution. The same ease of dilution is available for deep cleaning with Consolideck® LSKlean ULTRA 15 and LSKlean ULTRA 30.

Do not use acidic cleaners. Though Blended Densifier will improve the resistance of concrete surfaces to staining, acid concentrates and acidic foods may etch the floor and leave a residual stain. Clean up such spills quickly to minimize any potential for damage. Though protective treatments simplify maintenance of concrete floors, all spills must be cleaned up in a timely manner.

### WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine

## Product Data Sheet Consolideck® Blended Densifier

the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

### **CUSTOMER CARE**

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Field visits by PROSOCO personnel are for the purpose of making technical recommendations only. **PROSOCO is not responsible for providing job-site supervision or quality control. Proper application is the responsibility of the applicator.** Call Customer Care at 800-255-4255, or visit our web site at [prosoco.com](http://prosoco.com), for the name of the PROSOCO representative in your area.

