

# **H40**

Sure Klean® Weather Seal H40 is a deep-penetrating water repellent and consolidation treatment for brick, most natural stone, unglazed terra cotta, historic concrete, stucco and cast stone surfaces. H40 protects against deterioration caused by water and waterborne contaminants while strengthening weathered surfaces and soft mortar joints.

Weather Seal H40 also reduces the severity of biological staining common to regions with high relative humidity. It helps prevent the rapid recolonization of biological species such as mold, mildew and lichens that normally thrive on masonry and natural stone architecture.

## TYPICAL TECHNICAL DATA

| FORM             | Clear, slightly yellow liquid<br>Mild petroleum odor |  |  |
|------------------|--|--|--|
| SPECIFIC GRAVITY | 0.882  |  |  |
| pН               | not applicable                                       |  |  |
| WT/GAL           | 7.34 lbs   |  |  |
| ACTIVE CONTENT   | 23%  |  |  |
| TOTAL SOLIDS     | 21% ASTM D 2369                                      |  |  |
| VOC CONTENT      | >600 g/L   |  |  |
| FLASH POINT      | 99° F (37° C)<br>ASTM D3278                          |  |  |
| FREEZE POINT     | <-22° F (<-30° C)                                    |  |  |
| SHELF LIFE       | 2 years in tightly sealed,<br>unopened container     |  |  |

## **SAFETY INFORMATION**

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

24-Hour Emergency Information: INFOTRAC at 800-535-5053

## **ADVANTAGES**

- Deep penetration provides long-lasting protection.
- Strengthens and protects deteriorating surfaces.
- Strengthens soft mortar reduces need for repointing.
- Treated surfaces "breathe" does not trap moisture.
- H40 helps prevent rapid recolonization by biological species such as mold, mildew and lichens.
- Low odor.
- Resists water penetration when applied over existing shrinkage cracks of 0.02 inches or less

#### Limitations

- May damage glass or be difficult to remove. Always protect.
- May cause slight or moderate darkening on some surfaces. Always test for desired results.
- Surface and air temperatures should be above 40°F (4°C) and below 95°F (35°C). Avoid application on extremely windy days to avoid rapid evaporation of the solvent carrier.
- Not recommended for application to new concrete or below-grade application.
- Will not prevent water penetration through structural cracks, defects or open joints.

## **REGULATORY COMPLIANCE**

### **VOC Compliance**

Sure Klean® Weather Seal H40 is compliant with the US Environmental Protection Agency's AIM VOC regulations. Manufactured and marketed in compliance with US EPA AIM VOC regulations (40 CFR 59.403).

Visit www.prosoco.com/voccompliance to confirm compliance with individual district or state regulations.

# Product Data Sheet Weather Seal H40

### **PREPARATION**

Protect people, property, vehicles, plants and all non masonry surfaces from contact with the product, fumes and wind drift. Protect and/or divert pedestrian and auto traffic. H40 may damage some metal finishes and glass. Test and protect as necessary. PROSOCO's Strippable Masking is not effective protection for use with H40.

Ensure fresh air entry and cross ventilation during application and drying. Extinguish all flames, pilot lights and other potential sources of ignition during use and until all vapors are gone.

When applying to exteriors of occupied buildings make sure all windows, exterior intakes and air conditioning vents are covered and air handling equipment is shut down during application and until all vapors have dissipated. Fill all cracks and voids to keep fumes out of buildings.

Surface should be clean and free of dirt, dust, oils and other contaminants. If necessary, clean with

Recommended for these substrates. Always test.

Coverage is in sq.ft./m. per gallon.

| Substrate                            | Туре  | Use?                            | Coverage                      |
|--------------------------------------|---|---------------------------------|-------------------------------|
| Architectural<br>Concrete<br>Block   | Burnished<br>Smooth                               | yes<br>yes                      | 50–100 sq.ft.                 |
|                                      | Split-faced<br>Ribbed                             | yes<br>yes                      | 5–9 sq.m.                     |
| Concrete*                            | Brick Tile Precast Panels Pavers Cast-in-place    | yes<br>yes<br>yes<br>yes<br>yes | 75–175 sq.ft.<br>7–16 sq.m.   |
| Fired Clay                           | Brick<br>Tile<br>Terra Cotta (unglazed)<br>Pavers | yes<br>yes<br>yes               | 50–175 sq.ft.<br>5–16 sq.m.   |
| Marble•,<br>Travertine,<br>Limestone | Polished  | no                              | N/A                           |
|                                      | Unpolished  | yes                             | 100–175sq.ft.<br>9–16 sq.m.   |
| Granite•                             | Polished  | no                              | N/A                           |
|                                      | Unpolished  | yes                             | 150–400 sq.ft.<br>14–37 sq.m. |

\*Not suitable for application to new concrete.

•Slight darkening may occur.

yes

Unpolished

Unpolished

Sandstone

Slate\*

Always test to ensure desired results.

Coverage estimates depend on surface texture and porosity.

the appropriate PROSOCO cleaner. Surface must be thoroughly dry and absorbent before application.

All caulks and sealants should be in place and thoroughly cured before application. The top of walls should be capped and made watertight prior to application.

**NOTE**: Some floor and wall systems incorporate asphaltic or other crack-suppression membranes. This deeply penetrating protective treatment may penetrate through exposed stone, tile, grout or paver surfaces and react with the membrane to mobilize objectionable staining. Always pretest to ensure desired results.

### **Surface and Air Temperatures**

For maximum effectiveness, surface and air temperatures should be above  $40^{\circ}F$  ( $4^{\circ}C$ ) and below  $95^{\circ}F$  ( $35^{\circ}C$ ). Application on windy days may cause rapid evaporation of the solvent carrier and should be avoided.

### **Equipment**

Recommended application is by high volume, low-pressure (<50 psi) spray. Fit sprayers with solvent-resistant gaskets and hoses to avoid discoloration. Fan spray tips are recommended to avoid atomization. Do not atomize or vaporize the material.

For small scale application, or when spray application is not appropriate, product may be applied using brush or roller. Contact Customer Care or your local PROSOCO representative for more information. Brushes and rollers should be nylon or other synthetic material resistant to solvent solutions.

### **Storage and Handling**

Store in a cool, dry place away from potential ignition sources. Keep tightly closed when not dispensing. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperature of  $45\text{--}100^\circ\text{F}$  (7–38°C). Do not double stack pallets. Dispose of unused product and container in accordance with local, state and federal regulations.

### APPLICATION

Read "Preparation" and the Safety Data Sheet before use. ALWAYS TEST a small area of each surface to confirm suitability, coverage rates and desired results before starting overall application. Include in the test area any previous repairs and patches, including aesthetic cementitious finishes. Different surface compositions may result in absorption



75-200 sq.ft.

7-19 sq.m.

200-600 sq.ft.

19-56 sq.m.

# Product Data Sheet Weather Seal H40

and/or appearance differences. Test with the same equipment, recommended surface preparation and application procedures planned for general application.

### **Dilution & Mixing**

Apply as packaged. Do not dilute or alter.

### **Application Instructions**

#### **Vertical Surfaces**

### Spray Application

- 1. For best results, apply "wet-on-wet." Spray from the bottom up, saturating with enough material for a 6 to 8 inch rundown below the spray contact point.
- 2. Let the first application penetrate for 5–10 minutes
- 3. Reapply in the same saturating manner. Less material will be required on the second application.

### Brush or Roller Application

Recommended for small scale application or when spray application is not appropriate. Contact PROSOCO for more information. Take extra care to saturate the surface. Brush out heavy runs and drips that do not penetrate the surface after a few minutes.

**Horizontal Surfaces Application**: Saturate so the surface stays wet for a few minutes. Thoroughly broom out any pools or puddles that don't completely penetrate.

**Dense Surfaces Application**: Apply a single coat. Use enough to completely wet the surface without creating drips, puddles or rundown. Do not over apply. Always test for proper rate of application.

Strengthening Deteriorated Surfaces: For maximum strengthening benefits, apply H40 in as few as 1 and as many as 3 "cycles." Each cycle consists of 3 consecutive saturating applications applied at 5 to 10 minute intervals. Allow enough time between cycles (30–60 minutes) for penetration of the previous application.

### **Drving Time**

Protect the treated surface from rain and traffic for 4–6 hours after application. Highly absorbent horizontal surfaces may take several days before the damp appearance is gone. Weather Seal H40 gains its water-repellency properties in 72 hours.

#### Cleanup

Clean tools and equipment immediately with mineral spirits or an equivalent cleaning solvent.

Remove over spray and spills as soon as possible.

### **Painting Treated Surfaces**

Surfaces treated with Weather Seal H40 can be painted over with most high quality, oil-base and acrylic emulsion paints. Testing is always necessary to ensure adhesion.

### WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.

The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

## **CUSTOMER CARE**

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Field visits by PROSOCO personnel are for the purpose of making technical recommendations only. PROSOCO is not responsible for providing job-site supervision or quality control. Proper application is the responsibility of the applicator. Call Customer Care at 800-255-4255, or visit our website at prosoco.com, for the name of the PROSOCO representative in your area.