

## PRODUCT DATA SHEET

# LITHOCAST™ Surface Retarder

Water-based, biodegradable, low odor top surface retarder

### PRODUCT DESCRIPTION

LITHOCAST™ Surface Retarder is a water-based, biodegradable, low odor top surface retarder. Applied to the surface of fresh concrete, LITHOCAST™ Surface Retarder chemically delays the set of the surface mortar while allowing the underlying concrete to harden normally. This allows time for washing the surface, producing exposed aggregate flatwork, with subtle and varying reveals of texture and color.

### USES

Apply LITHOCAST™ Surface Retarder on gray concrete or concrete colored with CHROMIX® Admixtures for Color-Conditioned® Concrete.

Use on poured-in-place flatwork: curbs, sidewalks, driveways, patios, pool decks, tilt-up and precast panels, and most horizontal concrete installations.

### CHARACTERISTICS / ADVANTAGES

- Fully cured surface is attractive and slip resistant
- VOC compliant (<10 g/L)
- Solvent free
- LITHOCAST™ Surface Retarder is safer and cleaner to use compared to acid etching or mechanical blasting
- LITHOCAST™ Surface Retarder is available in multiple textures and colors

### PRODUCT INFORMATION

<b>Packaging</b>	LITHOCAST™ Surface Retarder is available in 1 gal. (3.8 L) and 5 gal. (19 L) pails.
<b>Appearance / Color</b>	LITHOCAST™ Surface Retarder 03 - Medium Sand Texture, white LITHOCAST™ Surface Retarder 05 - Coarse Sand Texture, light blue LITHOCAST™ Surface Retarder 15 - 1/8" to 1/4" Aggregate Exposure, green LITHOCAST™ Surface Retarder 50 - 3/8" to 1/2" Aggregate Exposure, blue LITHOCAST™ Surface Retarder 75 - Small Aggregate 3/8" Exposure, yellow LITHOCAST™ Surface Retarder 125 - 1/2" Aggregate Exposure, light green
<b>Shelf Life</b>	Shelf life in original, unopened containers is 2 years from the date of purchase.
<b>Storage Conditions</b>	Pails should be stored in a cool, dry place when not in use. Do not allow material to freeze. Do not reuse the empty container.

## TECHNICAL INFORMATION

---

### Specific Advice

#### Installation:

Proceed with application after approval of the test area. Utilize the same concrete mix design throughout the installation. Finish the concrete uniformly level. High or low areas may retain or reject the material, possibly creating inconsistencies in the exposed finish. Concrete with a float or broom finish allows LITHOCAST™ Surface Retarder to better penetrate the surface compared to hard-troweled concrete. Float open surfaces treated with an evaporation retarder or finishing aid before applying LITHOCAST™ Surface Retarder. Do not apply the material until bleed water has dissipated. Do not apply curing and sealing compounds before applying LITHOCAST™ Surface Retarder.

#### Existing Concrete:

The cement residue produced when removing LITHOCAST™ Surface Retarder will bond to hardened concrete. Protect existing concrete by covering it with plastic sheeting or by spraying it with LITHOCAST™ Surface Retarder. Allow LITHOCAST™ Surface Retarder to dry completely before proceeding with the new concrete installation. The dried film of LITHOCAST™ Surface Retarder will prevent the etched residue from penetrating or bonding to the concrete. Protect all adjacent surfaces from discoloration or damage from the chemical etching process.

---

## APPLICATION INFORMATION

---

### Coverage

LITHOCAST™ Surface Retarder will cover approximately 175–300 sq. ft./gal. (4.3–7.4 m<sup>2</sup>/L). Apply at full strength. Do not dilute. Coverage will vary with surface texture and application method.

---

### Equipment

Apply LITHOCAST™ Surface Retarder with a pump-up sprayer, brush, or roller. Spraying is the most effective and consistent method of application. Use clean equipment free from water or solvent residues. Clean application tools with clean water immediately after use.

---

## APPLICATION INSTRUCTIONS

### APPLICATION

Facilitate mixing by storing the material at moderate temperatures before use. Mix the material with a powered drill, do not hand mix. Mix at low speeds until the material is a uniform light blue color. Mixing time for a 5 gal. pail is 3–5 minutes. Apply an even coating of LITHOCAST™ Surface Retarder to the concrete's surface. When spraying, utilize the lowest pressure possible to create a fan pattern. Apply the material evenly, to achieve a masking, consistent blue color over the

concrete. If an insufficient amount of top surface retarder is applied, premature drying may occur, which could effect the exposure results. Heat, wind, and low humidity may also contribute to excessive drying. Cover the concrete surface completely with LITHOCAST™ Surface Retarder. For consistent exposure results, spray all concrete surfaces at the same time after completing concrete finishing.

#### Dwell Time:

Do not work the surface with a float or trowel after applying LITHOCAST™ Surface Retarder. The material will dry in 1–2 hours, after which time it is resistant to

light rain. Prior to drying, protect LITHOCAST™ Surface Retarder from rain by temporarily covering it with plastic and then removing as soon the weather allows. Divert downspouts or other sources of substantial water exposure from flowing directly on the concrete after applying LITHOCAST™ Surface Retarder. Do not apply curing compounds over the surface retarder.

#### **Removal and Exposure:**

Expose the aggregate by washing it within 6–24 hours after application, depending upon the temperature and humidity, and as determined by the approved mock-up panel. Use a garden hose and a new, clean broom or pressure washer to work the surface. Work a small area. If the depth of reveal is too deep, stop washing and allow the concrete to cure and harden further. Some concrete mix designs installed during elevated temperatures may require exposure to start sooner than 12 hours. Cold temperatures delay exposure. Achieve uniform exposure by washing the surface at the same time after the initial application of LITHOCAST™ Surface Retarder to the concrete.

#### **Curing and Sealing:**

Allow the concrete to dry (no visible moisture or dampness) for 12–24 hours before applying a liquid curing compound. Use SCOFIELD® CureSeal™ 350 or SCOFIELD® CureSeal™ 700 for exterior applications or interiors when a strong odor is not a concern. SCOFIELD® CureSeal-W™ is a waterbased system useful for interior and exterior applications. Multiple light coats are necessary over the roughened etched surface. Do not allow the material to puddle on the surface or in the joints. To protect the exposed aggregate finish, reseal the concrete with the same product originally used to cure.

#### **Quality Control:**

Create a job site sample at least 21 days before installation for approval. Utilize all materials, tools, and techniques from the actual job in the job site sample. When curing and sealing the surface, verify adequate wet and dry slip resistance of the sealed surface. Verify maintenance requirements.

## **LIMITATIONS**

Apply LITHOCAST™ Surface Retarder between 55 °F to 90 °F (13 °C to 32 °C). Most concrete mix designs stop curing below 50 °F. Do not allow the material to freeze during storage or after applied to the concrete. At higher

temperatures, low humidity, or windy conditions, the material may prematurely dry and lose its effectiveness unless it is reapplied. Do not apply to concrete that contains cold weather accelerators or hot weather retarders without prior testing. Do not apply to frozen surfaces, nor allow the material to freeze, before washing to expose the aggregate. Do not use as a finishing aid. The depth of etch will vary with different mix designs, method and timing of finishing, application consistency, temperature and removal method. Hard-troweled surfaces will reduce the effectiveness of LITHOCAST™ Surface Retarder. Do not apply to vertical concrete or to form work. Do not apply to shake-on color hardeners, particularly if the surface has a hardtroweled finish, without prior testing and approval. The very dense surfaces typically produced by shake-on color hardener may inhibit the depth of etch compared to a plain concrete surface finished in the same manner.

## **BASIS OF PRODUCT DATA**

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS**

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



**Product Data Sheet**  
LITHOCAST™ Surface Retarder  
January 2019, Version 01.01  
021405011000000051

**PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

LITHOCASTSurfaceRetarder-en-US-(01-2019)-1-1.pdf

