



DUST
REDUCED

Sika[®] Level-425

DUST REDUCED, SELF-LEVELING UNDERLAYMENT

- Innovative dust reduction technology
- Acceptable for castor wheel above 1/8" thickness
- Extremely low shrinkage

Available in
55 lb. bag



BUILDING TRUST



Sika® Level-425

DUST REDUCED, SELF-LEVELING UNDERLAYMENT

WHERE TO USE

- Interior use only
- Levels, flattens and smooths substrates before application of resilient floor
- Suitable on concrete, ceramic and quarry tile, OSB/Plywood, well bonded LVT
- Used in libraries, domestic properties, industrial facilities, cafeterias

FEATURES AND BENEFITS

- Innovative dust reduction technology
- Very low shrinkage
- Extremely high flow and smooth
- Compatible with subfloor heating systems
- Suitable for use in the Sika® Secure System
- Install most floor covering in 16 hours

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

| TYPICAL DATA (Material and curing conditions @ 73°F (23°C) and 50% R.H.) | |
|--|--|
| Color | Concrete Gray |
| Application Thickness | 1/8" up to 1/2" (3 mm up to 13 mm) Can be extended with aggregate to 1" (25 mm) |
| Density (ASTM C185) | 118 lbs/cu.ft. |
| Working Time | Approx. 30 minutes |
| Ready for Foot Traffic | Approx. 3 hours |
| Flexural Strength (ASTM C348) | 1,000 psi (6.9 MPa) at 28 days |
| Compressive Strength (ASTM C109) | 5,600 psi (38.6 MPa) at 28 days |
| VOC (EPA METHOD 24) | 0 g/l |

| Sika® Classification Table | | | | | |
|----------------------------|--|--|--|--|--|
| Strength | | | | | |
| Flow | | | | | |
| Depth | | | | | |
| Speed | | | | | |



FOR MORE INFORMATION:

Contact Sika: Phone 800.933.SIKA(7452) Website: www.sikasecure.com

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 201-933-8800
Fax: 201-933-6225



BUILDING TRUST

