

PRODUCT DATA SHEET

SikaGrout[®]-528 SF

High performance, cementitious grout with bleed resistance

PRODUCT DESCRIPTION

Non-shrink, non-metallic, cementitious grout with a unique two-stage shrinkage compensating mechanism. With a special blend of shrinkage-reducing and plasticizing/water-reducing agents, SikaGrout[®]-528 SF compensates for shrinkage in both the plastic and hardened states.

USES

- Use to grout and fill or repair voids in concrete
- Use for grouting tight clearances

PRODUCT INFORMATION

Packaging	50 lb (22.7 kg) bag
Appearance / Color	Gray powder
Shelf Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
Storage Conditions	Store dry at 40–95 °F (4–35 °C) Protect from moisture. If damp, discard material.

CHARACTERISTICS / ADVANTAGES

- Does not contain aluminum powder nor any components which generate hydrogen gas, carbon dioxide or oxygen.
- Enhanced with un-densified silica fume for low permeability
- Non-metallic, will not stain or rust
- Bleed resistant, even at high flow
- Low heat build-up
- Non-corrosive

TECHNICAL INFORMATION

Compressive Strength	1 day	2,000 psi (13.8 MPa)	(ASTM C-109)
	3 days	5,000 psi (34.5 MPa)	
	7 days	7,000 psi (48.3 MPa)	
	28 days	8,000 psi (55.2 MPa)	
Shrinkage	1 day	0.0 %	(ASTM C-1090) 73 °F (23 °C) 50 % R.H.
	28 days	0.0 to +0.2 %	
Expansion	3 hours	0.0 to +2.0 %	(ASTM C-940) 73 °F (23 °C) 50 % R.H.
Bleeding	4 hrs	0.0 %	(ASTM C-940*)
* Modified per FL Dot Wick Induced Bleed Test			
Rapid Chloride Permeability	< 2,500 C		(ASTM C-1202 AASHTO T-277)
Electrical Resistivity	28 days	< 10,000 ohm.cm	(ASTM C-1202)
Corrosion Test	Time to corrosion control	344 hrs	(Reference FL DOT Specification Section 938-6)
SikaGrout®-528 SF > 1,000 hrs. (Independent lab results available upon request)			

APPLICATION INFORMATION

Mixing Ratio	11.5–12.5 pts (5.4–5.9 L) of water per bag Do not exceed 12.5 pints of water		
Fresh Mortar Density	125 lb/ft ³	(ASTM C-138)	
Coverage	0.48 ft ³ (0.01 m ³) per bag (Coverage figures do not include allowance for surface profile and porosity or material waste)		
Layer Thickness	Min. 1/8" (3 mm)		
Flowability	After mixing	7–20 sec.	(ASTM C-939*)
	After 30 min.	7–20 sec.	
* Modified per FL DOT Section 938 and PTI Section 4.4.5.2.			
Product Temperature	65–75 °F (18–24 °C)		
Ambient Air Temperature	40–100 °F (4–38 °C)		
Substrate Temperature	40–100 °F (4–38 °C)		
Pot Life	Material must be placed within 60 minutes of mixing.		
Set Time	3–12 hours initial set	(ASTM C-266)	

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- Surface must be clean and sound. Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- To ensure optimum repair results, the effectiveness of decontamination and preparation should be assessed by a pull-off test.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.
- Ensure any forms will retain grout without leakage.

MIXING

- For best results use a colloidal mixer similar to ChemGrout® CG-600 series or other type of high shear mixer at approximately 1,800 rpm.
- Start by using 11.5 pints (5.4 L) of water at approximately 70°F (If higher, use cold water; if colder, use warm water.) per bag in a clean and appropriate mixing vessel.
- Add bag of material to mixing vessel.
- Mix for minimum of 3 minutes after the addition of the last bag or until a homogeneous mix is achieved.
- Continue to agitate material in the holding hopper to achieve best flow.
- Only add additional water as needed up to a total maximum of 12.5 pints (5.9 L) (DO NOT EXCEED) per bag in order to achieve the flow specified on the Product Data Sheet (PDS).
- At higher temperatures and/or water amounts near upper range of maximum 12.5 pints (5.9 L), the grout will be less thixotropic. Therefore, it may be more appropriate to measure the flow using the standard flow cone test (ASTM C-939).
- Alternatively, for quantities less than 1 bag, mechanically mix with high-speed drill (2,500 rpm) and Sika jiffy paddle for a minimum of 6 minutes.
- Method of mixing may significantly affect the material properties, particularly flow.
- Project specific testing by the engineer is recommended to ensure that the mixing and placement methods result in the specified requirements.

APPLICATION

- Make sure all forming, mixing, placing, and clean-up materials are on hand.
- A mock-up should be completed on-site and inspected by the engineer to ensure that the placement means and methods yield the specified results.

LIMITATIONS

- Do not use as a patching or overlay mortar or in unconfined areas.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® 32 Hi-Mod.
- Do not use in post tensioning applications

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

0 g/l

(EPA method 24)

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

SikaGrout®-528 SF
March 2020, Version 01.02
020201010010000232

SikaGrout-528SF-en-US-(03-2020)-1-2.pdf

