

## PRODUCT DATA SHEET

# Sikacrete<sup>®</sup>-211 SCC Plus

One-component, cementitious, polymer-modified, self consolidating concrete mix with an integral migrating corrosion inhibitor

### PRODUCT DESCRIPTION

Sikacrete<sup>®</sup>-211 SCC Plus is a one-component, self consolidating concrete containing factory blended coarse aggregate. This self consolidating concrete bag is silica fume and polymer modified and also contains a migrating corrosion inhibitor.

### USES

- Full depth repairs
- On grade, above and below grade on concrete
- On horizontal surfaces
- Vertical and overhead surfaces when formed and pumped or poured
- As a structural repair material for parking facilities, industrial plants, walkways, bridges, tunnels, dams, and balconies
- Filler for voids and cavities

### CHARACTERISTICS / ADVANTAGES

- Self Consolidating Concrete - Excellent placement characteristics
- Polymer-modified
- Integral penetrating corrosion inhibitor
- Silica fume enhanced
- Prepackaged coarse aggregate. Eliminates the need to extend material in the field. Eliminates the risk of reactive aggregate
- Can be pumped or poured into forms and gets excellent consolidation without vibrating

### PRODUCT INFORMATION

<b>Packaging</b>	65 lb. (29.5 kg) bag
<b>Appearance / Color</b>	Gray powder
<b>Shelf Life</b>	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
<b>Storage Conditions</b>	Store dry at 40–95 °F (4–35 °C) Protect from moisture. If damp, discard material

## TECHNICAL INFORMATION

<b>Compressive Strength</b>	1 day	2,000 psi (13.8 MPa)	(ASTM C-39) 73 °F (23 °C) 50 % R.H.
	7 days	5,500 psi (37.9 MPa)	
	28 days	6,500 psi (44.8 MPa)	
<b>Flexural Strength</b>	1 day	500 psi (3.4 MPa)	(ASTM C-293) 73 °F (23 °C) 50 % R.H.
	7 days	750 psi (5.2 MPa)	
	28 days	1,000 psi (6.9 MPa)	
<b>Splitting Tensile Strength</b>	7 days	750 psi (5.2 MPa)	(ASTM C-496) 73 °F (23 °C) 50 % R.H.
	28 days	1,000 psi (6.9 MPa)	
<b>Tensile Adhesion Strength</b>	1 day	250 psi (1.7 MPa)	(ASTM C-1583) 73 °F (23 °C) 50 % R.H.
	7 days	300 psi (2.1 MPa)	
<b>Slant Shear Strength</b>	1 day	1,000 psi (6.9 MPa)	(ASTM C-882 modified)*
	7 days	1,500 psi (10.3 MPa)	
	28 days	2,500 psi (17.2 MPa)	
* Mortar scrubbed into substrate at 73 °F (23 °C) and 50 % R.H.			
<b>Shrinkage</b>	28 days	< 0.05 %	(ASTM C-157 modified)
<b>Freeze-Thaw Stability</b>	300 cycles	> 99 %	(ASTM C-666)
<b>Freeze Thaw De-Icing Salt Resistance</b>	50 cycles	2	(ASTM C-672)
<b>Sulfate Resistance</b>	0.006*		(ASTM C-1012)
*Length change after 6 months at 73 °F (23 °C) and 50 % R.H.			
<b>Rapid Chloride Permeability</b>	28 days	< 650 Coulombs	(ASTM C-1202 AASHTO T-277)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	5.5-6 pints (2.6-2.8 L)		
<b>Coverage</b>	0.50 ft <sup>3</sup> (0.01 m <sup>3</sup> ) per bag (Coverage figures do not include allowance for surface profile and porosity or material waste)		
<b>Layer Thickness</b>	<b>Min.</b>	<b>Max.</b>	
	1" (25 mm)	8" (203 mm)	
<ul style="list-style-type: none"> <li>▪ Thicker applications have been done successfully.</li> <li>▪ Please consult Sika® Technical Service.</li> </ul>			
<b>Consistency</b>	Initial spread	25-30" (6.4-7.6 cm)	(ASTM C-1611)
	Spread at 30 min.	> 15" (3.9 cm)	
<b>Product Temperature</b>	65–75 °F (18–24 °C)		
<b>Ambient Air Temperature</b>	> 45 °F (7 °C)		
<b>Substrate Temperature</b>	> 45 °F (7 °C)		
<b>Pot Life</b>	~ 60 minutes		
	As the temperature will affect the pot life, application temperature: <ul style="list-style-type: none"> <li>▪ Above 73 °F (23 °C) will reduce the pot life and slump</li> <li>▪ Below 73 °F (23 °C) will extend the pot life and slump</li> </ul>		

# APPLICATION INSTRUCTIONS

## SURFACE PREPARATION

### Concrete

- Surface must be clean and sound. Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- Be sure repair area is not less than 1" (25 mm) deep.
- Preparation work should be done by appropriate means. Obtain an exposed aggregate surface with a minimum surface profile of  $\pm 1/8"$  (3 mm) (CSP-7-8) on clean, sound concrete.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.

### Reinforcing Steel

- Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust.
- Where corrosion has occurred, the steel should be high-pressure washed with clean water after mechanical cleaning.
- For priming and protection of reinforcing steel use Sika® Armatec® 110 EpoCem (consult PDS).

## MIXING

- Start mixing with 5.5 pints (2.6 L) of water.
- An additional 0.5 pint (0.2 L) can be added if needed.
- Do not over water as excess water will cause segregation.
- Add Sikacrete®-211 SCC Plus while continuing to mix.
- Mechanically mix to a uniform consistency, for 3 minutes with a low-speed drill (400–600 rpm) and paddle or in appropriate-size mortar mixer or concrete mixer.

## APPLICATION

- Pre-wet surface to SSD.
- Ensure good intimate contact with the substrate is achieved. To accomplish this, material should be scrubbed into the substrate or other suitable means should be employed such as vibration of the material or pumping under pressure.
- Vibrate form while pouring or pumping.
- Pump with a variable pressure pump.
- Continue pumping until a 3 to 5 psi increase in normal line pressure is evident then STOP pumping.
- Form should not deflect.
- Vent to be capped when steady flow is evident, and forms stripped when appropriate.

## CURING TREATMENT

- As per ACI recommendations for Portland cement concrete, curing is required.
- Moist cure with wet burlap and polyethylene, a fine mist of water or Sika® Antisol®-250 W\*.
- Curing compounds adversely affect the adhesion of following layers of mortar, leveling mortar or

- protective coatings.
- Moist curing should commence immediately after finishing.
- Protect newly applied material from direct sunlight, wind, rain and frost.

\* Pretesting of curing compound is recommended.

## LIMITATIONS

- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts, with an appropriate epoxy such as Sikadur® 32 Hi-Mod.
- Refer to Sika® Antisol®-250 W product data sheet for use.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

0 g/L

(EPA Method 24)

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the

obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



**Product Data Sheet**

Sikacrete®-211 SCC Plus  
March 2020, Version 01.04  
020302020010000040

Sikacrete-211SCCPlus-en-US-(03-2020)-1-4.pdf

