

Sikadur® 22 Lo-Mod NEW (AB)

Low-modulus, medium-viscosity, epoxy resin binder

Description	Sikadur® 22, Lo-Mod is a 2-component, 100% solids, moisture-tolerant, epoxy resin binder. It conforms to the current ASTM C-881, Type III, Grade-2, Class-C and AASHTO M-235 specifications.
Where to Use	Use neat as the binder resin for a skid-resistant broadcast overlay. Use also as the binder resin for epoxy mortar and concrete for patching and overlays.
Advantages	<ul style="list-style-type: none"> ■ Tolerant to moisture both before and after cure. ■ Convenient easy mix ratio A:B = 1:1 by volume. ■ Excellent strength development. ■ Leveling viscosity for easy, efficient application of a broadcast overlay. ■ Material is USDA-certifiable
Coverage	1 gal. yields 231 cu. in. Mortar Binder - 1 gal. of mixed Sikadur® 22 Lo-Mod with the addition of 5 gal. by loose volume of an oven dried sand, yields approximately 808 cu. in. of epoxy mortar.
Packaging	4 gal. units

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life:	2 years in original, unopened containers.		
Storage Conditions:	Store dry at 40°-95°F (4°-35°C).		
Condition material:	65°-85°F (18°-29°C) before using.		
Color: Clear to light amber.			
Mixing Ratio:	Component 'A':Component 'B' = 1:1 by volume.		
VOC:	<50 gm/L		
Viscosity:	Approximately 2,000 cps.		
Gel Time:	Approximately 15-20 minutes. (60 gram mass; ASTM C881)		
Tack-Free Time:	40°F (4°C)	73°F (23°C)	90°F (32°C)
	8 hrs	2.5-3 hrs	2 hrs
Traffic Time:	24 hrs	3.5 hours	2.5 hrs
Tensile Properties (ASTM D-638) Mortar 1:3 Neat			
7 day Tensile Strength	1200 2600		
Elongation at Break:	~50%		
Shear Strength (ASTM D-732) Mortar 1:3 Neat			
7 day Shear Strength	2600 3430		
Water Absorption (ASTM D-570) Neat			
7 day (24 hour immersion)	<0.20%		
Abrasion (Taber Abrader) Mortar 1:3 Neat			
14 day Weight loss	1,000 cycles	2.0 grams	0.030 gms
(H-22 wheel; 1,000 gm weight for mortar/C-17 wheel, 1,000 gm wt for neat)			
Hardness (Shore D - ASTM D-2240)	72		
Chloride Permeability	0 coulombs		
Direct Pull Off Bond Test (ASTM C1583) Mortar			
1 day	>550 psi (concrete failure)		
7 day	>570 psi (concrete failure)		
Compressive Properties (ASTM D-695) Mortar 1:3			
Thermal Compatibility (ASTM C884)	Pass		
Compressive Strength, psi	40°F*(4°C)	73°F* (23°C)	90°F*(32C)
3 hour	1800 psi	3600 psi	-
8 hour	2000 psi	4400 psi	6400 psi
1 day	4500 psi	6500 psi	8000 psi
3 day	5500 psi	7500 psi	8500 psi
7 day	8500 psi	8500 psi	9000 psi
14 day	9000 psi	9000 psi	9000 psi
28 day	9000 psi	9000 psi	9000 psi

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.



Compressive Modulus	
7 day	40,000 psi
28 day	40,000 psi
* Material cured and tested at the temperatures indicated	

How to Use

Surface Preparation Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes and any other contaminants.

Preparation Work:

Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means.

Steel - Should be cleaned and prepared thoroughly by blast cleaning or equivalent mechanical means to white metal finish.

Mixing Pre-mix each component. Take care as premixing of unfilled resins may entrain excessive air. Proportion equal parts by volume of Component 'A' and 'B' into clean pail. Mix thoroughly for 3 min. with Sika paddle on low-speed (400-600 rpm) drill until uniformly blended. Mix only that quantity that can be used within pot life.

To prepare epoxy mortar - Slowly add 5 parts by loose volume of oven-dried sand to 1 part of mixed Sikadur® 22 Lo-Mod until uniform in consistency.

Application Broadcast Overlay - Prime the prepared substrate with Sikadur® 22 Lo-Mod. While primer is still tacky, spread mixed Sikadur® 22 Lo-Mod with a 3/16 in. notched squeegee. When material levels, broadcast the oven-dried aggregate slowly allowing it to settle in the epoxy binder. Ultimately the broadcast aggregate should be applied to excess at a rate of 2 lbs./ft². Remove excess broadcast aggregate after epoxy has set. Priming is an optional step in the broadcast overlay applications.

Epoxy Mortar - Prime prepared substrate with mixed Sikadur® 22 Lo-Mod or Sikadur® 21 Lo Mod LV. While primer is still tacky, apply epoxy mortar by trowel or vibrating screed. Finish with finishing trowel. Priming is mandatory when using the 22 Lo Mod as an epoxy mortar.

- Limitations**
- Minimum substrate and ambient temperature 40°F (4°C).
 - Porous substrates must be tested for moisture-vapor transmission prior to application. (Ref. ASTM D-4263)
 - Minimum age of concrete before application is 21-28 days depending upon curing and drying conditions.
 - Do not use on exterior slab on grade.
 - Maximum thickness 1/2 in. (13 mm) exterior exposed to thermal change.
 - Do not dilute. Addition of solvents will prevent proper cure.
 - Use oven-dried aggregates only.
 - Material is a vapor barrier after cure.
 - Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537

