

PRODUCT DATA SHEET

Sikadur[®]-55 SLV

SUPER LOW-VISCOSITY, MOISTURE-TOLERANT EPOXY RESIN, CRACK HEALER/PENETRATING SEALER

PRODUCT DESCRIPTION

Sikadur[®]-55 SLV is a 2-component, 100 % solids, moisture-tolerant, epoxy crack healer / penetrating sealer, having a fast tack-free time to minimize downtime. It is a super low-viscosity, high-strength adhesive formulated specifically for sealing both dry and damp, existing, non-dynamic cracks. It conforms to the current ASTM C-881, Types I and II, Grade-1, Class-C* and AASHTO M-235 specifications.

* except for gel time

USES

Sikadur[®]-55 SLV may only be used by experienced professionals.

- Sikadur[®]-55 SLV seals cracked concrete.
- For interior slabs and exterior above-grade slabs.
- For elevated horizontal decks, parking garages and other structures exposed to foot and pneumatic tire traffic.

CHARACTERISTICS / ADVANTAGES

- Super low viscosity/low surface tension for excellent penetration into existing cracks.
- Seals existing cracks by gravity down to 2 mils (0.002" / 0.05 mm) in width.
- Prolongs life of cracked concrete.
- Penetrates and seals surface from water absorption, chloride-ion intrusion, and chemical attack (patent pending technology).
- Improves concrete surface by reducing water and chloride intrusion.
- Can be open to traffic in 6 hours at 73 °F (23 °C).
- High bond strength, even in damp cracks.
- U.S. Patent No. (pending) for ultra low viscosity healer/sealer to strengthen cracked concrete.

PRODUCT INFORMATION

Packaging	3 gal. (11.35 l) unit = 'A' = 2 gal. (7.6 l) + 'B' = 1 gal. (3.8 l)
Color	Clear, amber
Shelf Life	2 years in original, unopened containers
Storage Conditions	Store dry at 40–95 °F (4–35 °C). Condition material to 65–75°F (18–24 °C) before using.
Viscosity	Approximately 105 cps

TECHNICAL INFORMATION

Compressive Strength	40°F (4°C)	60°F (15°C)	73°F (23°C)	90°F (32°C)
1 day	-	320 psi (2.2 MPa)	1,100 psi (7.6 MPa)	4,800 psi (33.1 MPa)
3 days	2,000 psi (13.8 MPa)	6,500 psi (44.8 MPa)	8,300 psi (57.2 MPa)	8,000 psi (55.2 MPa)
7 days	7,800 psi (53.8 MPa)	10,400 psi (71.7 MPa)	10,900 psi (75.1 MPa)	8,300 psi (57.2 MPa)
14 days	9,600 psi (66.2 MPa)	11,000 psi (75.8 MPa)	11,800 psi (81.4 MPa)	10,000 psi (68.9 MPa)
28 days	11,700 psi (80.7 MPa)	12,000 psi (82.7 MPa)	12,000 psi (82.7 MPa)	10,000 psi (68.9 MPa)

Flexural Strength	8,500 psi (58,6 MPa) (7 days)	(ASTM D-790) 73 °F (23 °C) 50 % R.H.
Modulus of Elasticity in Flexure	3.2 x 10 ⁵ psi (2,206 MPa) (7 days)	(ASTM D-790) 73 °F (23 °C) 50 % R.H.
Tensile Strength	7,100 psi (48,9 MPa) (7 days)	(ASTM D-638) 73 °F (23 °C) 50 % R.H.
Elongation at Break	10 % (7 days)	(ASTM D-638) 73 °F (23 °C) 50 % R.H.
Tensile Adhesion Strength	<p>Hardened Concrete to Hardened Concrete</p> <p>2 day (moist cure) 2,500 psi (17.2 MPa)</p> <p>14 day (moist cure) 2,500 psi (17.2 MPa)</p> <p>Hardened Concrete to Steel</p> <p>2 day (moist cure) 1,500 psi (10.3 MPa)</p> <p>14 day (moist cure) 1,600 psi (11.0 MPa)</p>	<p>(ASTM C-882) 73 °F (23 °C) 50 % R.H.</p> <p>(ASTM C-882) 73 °F (23 °C) 50 % R.H.</p>
Shear Strength	5,800 psi (40.0 MPa) (7 days)	(ASTM D-732) 73 °F (23 °C) 50 % R.H.
Heat Deflection Temperature	[fiber stress loading = 264 psi (1.8 MPa) 110 °F (43 °C) (7 days)	(ASTM D-648)
Water Absorption	0.60 % (7 days, 24 hour immersion)	(ASTM D-570)

APPLICATION INFORMATION

Mixing Ratio	Component 'A' : Component 'B' = 2:1 by volume
Coverage	1 gal. (3.8 liters) yields 231 cu. in. (3,785 cm ³) Typical coverage is 150–175 ft ² /gal. (3.7–4.3 m ² /L) for surface sealing. Coverage varies with porosity and surface profile of substrate. Higher porosity concrete will reduce coverage. For crack healing, follow Application instructions and allow to pond over cracks.

Pot Life Approximately 20 minutes

Cure Time	Tack-Free Time			
	40 °F (4 °C)	60 °F (15 °C)	73 °F (23 °C)	90 °F (32 °C)
	>11 h	11 h	6 h	2.5 h

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Substrate must be clean, sound and free of surface moisture. Remove dust, laitance, grease, oils, curing compounds, waxes, impregnations, foreign particles, coatings and disintegrated materials by mechanical means (i.e. shot blasting, sandblasting, etc.). For best results, substrate should be dry. Surfaces prepared by Low Pressure Water Cleaning or High Pressure Water Jetting methods should be allowed to dry for 24 hrs. minimum [at 73 °F (23 °C)].

MIXING

Mix 1 part Component 'B' to 2 parts Component 'A' by volume into a clean pail. Mix thoroughly for 3 minutes with Sika paddle or jiffy mixer on a low-speed (400–600 rpm) drill until uniformly blended. Mix only that quantity which can be used within its pot life.

APPLICATION METHOD / TOOLS

To gravity feed cracks: Sikadur®-55 SLV is applied to horizontal surfaces by flat squeegee or broom. Spread material over area and allow to pond over cracks. Let material penetrate into cracks and substrate. Remove excess epoxy with roller leaving no visible surface film. For cracks greater than 1/8 in. (3 mm) wide, fill crack with oven-dried sand before applying Sikadur®-55 SLV. Seal cracks from underside, when accessible, to prevent leakage. A second treatment may be required on very porous substrates. Apply second treatment before broadcasting. After treatment, wait a minimum of 20–30 minutes at 73 °F (23 °C) before broadcasting sand. Cover with broadcast of an oven-dried 20/40 silica sand or similar sand. Distribute evenly over the surface to excess at a rate of 30-40 lbs./100 sq. ft.. Allow to cure 6 hours minimum at 73 °F (23 °C). Remove any loose sand and open to traffic once epoxy has cured. Consult Sika Technical Service at 1-800-933-SIKA for additional information.

To pressure inject cracks: Use automated injection equipment. Set appropriate injection ports. Seal ports and cracks with Sikadur® 31, Hi-Mod Gel, Sikadur® Injection Gel or Sikadur® AnchorFix 2/Sikadur® AnchorFix 500. When the epoxy adhesive has cured, inject Sikadur®-55 SLV with steady pressure. Consult Technical Service at 1-800-933- SIKA for additional information. Mock ups to ascertain penetration on job site conditions is strongly recommended. Actual penetration should be verified by core testing.

LIMITATIONS

- Do not thin. Addition of solvents will prevent proper cure.
- Material is a vapor barrier after cure.
- Do not apply if rain is imminent. Water exposure or humidity will affect surface appearance and may cause surface whitening.
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure.
- Sealed concrete surface may appear blotchy due to differential absorption.
- Allow sufficient time for the substrate to dry after rain or other inclement conditions.
- Application temperature of substrate must be minimum 5 °F (3 °C) above the dew point.
- Minimum ambient and substrate temperature 40 °F (4 °C). Maximum application temperature 95 °F (35 °C).
- Do not inject cracks greater than 1/4 in. (6 mm) Consult Technical Service at 1-800-933-SIKA.
- Minimum age of concrete is 21–28 days, depending on curing and drying conditions.
- Not designed to seal or inject cracks under hydrostatic pressure during application.
- Penetration results will vary. Factors that may impede penetration include, but are not limited to, temperature (ambient and material), geometry of crack, concrete porosity, and dirt inside cracks.
- Product is not appropriate for use in dynamic cracks.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

Para información y consejo sobre seguridad en la manipulación, almacenamiento y disposición de productos químicos, los usuarios deben referirse a la ficha de datos de seguridad vigente, la cual contiene datos físicos, ecológicos, toxicológicos y otros datos relativos a la seguridad. En caso de emergencia llamar al CITUC a los siguientes fonos: 26353800 por intoxicaciones ó 22473600 por emergencias químicas.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: +1-800-933-7452
 Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
 Carretera Libre Celaya Km. 8.5
 Fracc. Industrial Balvanera
 Corregidora, Queretaro
 C.P. 76920
 Phone: 52 442 2385800
 Fax: 52 442 2250537



Product Data Sheet
 Sikadur®-55 SLV
 October 2018, Version 01.01
 020204030010000190

Sikadur-55SLV-en-US-(10-2018)-1-1.pdf

BUILDING TRUST

