



Sikaflex[®]-1a

Premium-grade, all purpose polyurethane sealant, for professional caulking and sealing contractors



Sikaflex®-1a

Professional-grade polyurethane sealant

APPLICATIONS

- ▲ Building facades
- ▲ Balconies
- ▲ Parking Structures
- ▲ Civil Structures

ADVANTAGES

- ▲ Fast tack-free time and final cure
- ▲ Easy to use
- ▲ Creamy, easy to tool
- ▲ Excellent Adhesion
- ▲ Excellent resistance to weathering
- ▲ Paintable and sandable
- ▲ High Elasticity
- ▲ Acceptable for traffic areas
- ▲ Water immersible
- ▲ Meets 1998 USDA guidelines

TYPICAL DATA

- ▲ Tack-free time 3-6 hours
- ▲ Final Cure 4-7 days
- ▲ Joint Movement +/-35%
- ▲ Elongation 550%
- ▲ Shore A Hardness 40 +/- 5
- ▲ Meets ASTM C-920. Meets Federal specification TT-S-00230C, Type II, Class A. , Type S, Grade NS, Class 35, use T, NT, O, M, G, I; Canadian Standard CAN/CGSB 19.13-M87
- ▲ Sealant, Waterproofing and Restoration Institute (SWRI) validated
- ▲ UL Certified to NSF/ANSI Standard 61 for potable water contact

* For up to date and accurate information please consult the current Technical Data Sheet at www.sikausa.com



Available in 10.1 oz. cartridges and 20 fl. oz. uni-pac sausages; special order-5 gallon pails and 55 gallon drums.

SEALANT-WATERPROOFING & RESTORATION INSTITUTE

Issued to: Sika Corporation
Product: Sikaflex®-1A

C719: Pass Ext:+35% Comp:-35%

Substrate: Mortar, Aluminum, Glass
[mortar substrate primed with Sika Primer 429]

C661: Rating 40

Validation Date: 8/3/12 - 8/2/17

No. 0812-S11211 Copyright © 2012

SEALANT VALIDATION
www.swrionline.org

Contact Sika at:
Phone: 1-800-933-SIKA (Nationwide)
Website: www.sikausa.com

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 201-933-8800
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792



Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537