

PRODUCT DATA SHEET

Sikaflex-410 Asphalt Sealant

One Component, Self-leveling, Hybrid Sealant

PRODUCT DESCRIPTION

Sikaflex-410 Asphalt Sealant is a premium grade, one component, self-leveling, elastomeric, hybrid sealant.

USES

Sikaflex-410 Asphalt Sealant may be used by experienced professionals as well as do-it-yourselfers.

For joint sealing and crack repairs on:

- Asphalt driveways
- Asphalt roadways / walkways
- Asphalt pavements
- Asphalt to concrete joints
- Aprons, approaches, etc.

CHARACTERISTICS / ADVANTAGES

- Single component, no mixing
- Self-leveling consistency
- Fast skin time (< 60 minutes)
- Permanently elastic
- High durability
- Resists aging, weathering
- Excellent adhesion

PRODUCT INFORMATION

Packaging	9 fluid ounce (266 ml), moisture resistant, caulk gun cartridges 6 cartridges per case
Color	Black
Shelf Life	12 months from date of production when stored properly in original, unopened and undamaged, sealed packaging.
Storage Conditions	Store in cool, dry, well ventilated conditions at 40 - 90 °F (4 - 32 °C). Condition cartridge material to 65 - 75 °F (18 - 24 °C) before using.

TECHNICAL INFORMATION

Shore A Hardness	20 ± 5 (7 days)	(ASTM D 2240), 73 °F (23 °C), 50% R.H.
Movement Capability	± 25%	
Resistance to Weathering	Excellent	

APPLICATION INFORMATION

Coverage	9 fluid ounce (266 ml) Cartridge: Typical Yield in Linear Feet (linear meters)			
	1/4 inch (6 mm) Depth	3/8 inch (10 mm) Depth	1/2 inch (13 mm) Depth	
Width				
1/4 inch (6 mm)	21.6 (6.6)	14.4 (4.4)	10.8 (3.3)	
3/8 inch (10 mm)	14.4 (4.4)	9.6 (2.9)	7.2 (2.2)	
1/2 inch (13 mm)	10.8 (3.3)	7.2 (2.2)	5.4 (1.6)	
3/4 inch (19 mm)	7.2 (2.2)	4.8 (1.5)	3.6 (1.1)	
1 inch (25 mm)	5.4 (1.6)	3.6 (1.1)	2.7 (0.8)	
Coverage values are theoretical, based on calculation and do not include waste.				
Ambient Air Temperature	50 °F (10 °C) minimum / 100 °F (38 °C) maximum			
Substrate Temperature	50 °F (10 °C) minimum / 100 °F (38 °C) maximum			
Skin Time	Less than 60 Minutes (1 hour) at 73 °F (23 °C) and 50% Relative Humidity			

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

- The ultimate performance of fully cured Sikaflex-410 Asphalt Sealant depends on good joint design and proper substrate preparation and application.
- Minimum age of concrete must be 21 - 28 days depending upon curing and drying conditions.
- Do not apply when moisture vapor transmission exists since this can cause bubbling within the sealant.
- Minimum depth of sealant in a working dynamic joint is 1/4 inch (6 mm). Maximum depth of sealant is 1/2 inch (13 mm).
- Typical minimum width of sealant in a working dynamic joint is 1/4 inch (6 mm). Typical maximum width of sealant is 1 inch (25 mm).
- Avoid contact with alcohols and other solvents during and after cure. Do not use water, saliva, a soapy solution, alcohol or solvent as a finishing aid when tooling. Sikaflex-410 Asphalt Sealant has a pourable, self-leveling consistency. Dry tool finish only if required, although minimal tooling should be needed.
- Since the system is moisture-cured, permit sufficient exposure to air.
- Lower temperatures and humidity levels will extend skin time and final cure time.
- Allow a minimum 7 days of cure before subjecting sealant to water immersion.
- When overcoating, allow a minimum 7 days of cure. A jobsite test and mockup are essential to determine actual compatibility before proceeding with coating installation. Avoid alcohol based or solvent

based primers, sealers, stains and coatings. Consult directly with the coating manufacturer before proceeding.

- Rigidly curing primers, paints, coatings, etc. may crack when placed over elastomeric sealants subject to expansion and/or contraction.
- Not suitable for:
 - Anticipated joint movement greater than $\pm 25\%$.
 - Joints that occur on sloped surfaces.
 - Improperly prepared or contaminated joint void surfaces.
 - Treating joints subject to hydrostatic pressure (i.e. actively leaking or with the presence of standing water) at time of installation.
 - Joints where adhesion to painted surfaces is needed. Paint should be mechanically removed. If not, then adhesion and compatibility tests are required before proceeding.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage, and disposal of chemical products, user should refer to the actual current Safety Data Sheets containing physical, environmental, toxicological, and other safety related data. User must read the actual current Safety Data Sheets before using any products. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All joint surfaces must be clean, sound, free of contaminants, dust free, dry and frost free. Interior joint contact surfaces must be free of previous joint sealing materials, oils, grease, loose tar, paints, coatings, sealers, curing compound residues, rust and any other foreign matter that might prevent good adhesion. Asphalt should be prepared to clean, sound, dust free, dry, and frost free conditions. Concrete substrate preparation should be accomplished by mechanical means (e.g. sandblasting, abrasive grinding, etc.). Mask off and protect any adjacent surfaces (e.g. edges of joint) that should not receive contact with Sikaflex-410 Asphalt Sealant. Closed cell backer rod or bond breaker tape must be installed at the bottom or base of a dynamically working joint prior to sealant installation to prevent three sided adhesion. Closed cell backer rod diameter should be larger (i.e. typically up to 25% larger) than the actual width of the joint to provide a friction fit and adequate sealant support. Bond breaker tape, when used in lieu of closed cell backer rod, should cover the bottom or base of the joint void.

Joint Design: Proper joint design for working joints is 2:1 width to depth ratio (typical), with a recommended minimum 1/4 inch (6 mm) and maximum 1/2 inch (13 mm) depth of sealant. For nonmoving joints, the width to depth ratio can vary. For traffic bearing joints, the maximum recommended 1/2 inch (13 mm) depth of thickness should be considered over appropriate closed cell backer rod or bond breaker tape. Consult with Sika Technical Services for unusual joint configurations.

APPLICATION METHOD / TOOLS

Recommended application (i.e. ambient and substrate) temperatures: 50 to 100 °F (10 to 38 °C). Condition sealant cartridge to 65 to 75 °F (18 to 24 °C) before using. Cut the plastic tip at an angle to the desired size and puncture the airtight seal within, at the base of the tip. NOT FOR SLOPED SURFACES. The maximum sealant depth is 1/2 in. (13 mm) and width is 1 inch (25 mm). The minimum sealant depth is 1/4 in. (6 mm) and width is 1/4 in. (6 mm). Dispense sealant into the joint slot over either closed cell backer rod or bond breaker tape in one direction and allow the sealant to flow and level out as necessary. Tool as required, although minimum

tooling is necessary. Ideal, proper design is a 2:1 width to depth ratio over closed cell backer rod or bond breaker tape. Always use bond breaker tape or closed cell backer rod for support on horizontal joints.

CLEANING OF TOOLS

Uncured Sikaflex-410 Asphalt Sealant can be removed from tools and finished surfaces using an approved solvent (e.g. Acetone, MEK or Xylene). Cured Sikaflex-410 Asphalt Sealant can only be removed from surfaces mechanically. For spillage, collect, absorb, and dispose of in accordance with current, applicable local, state, and federal regulations. Consult the current Safety Data Sheet for additional information.

OTHER RESTRICTIONS

See Legal Disclaimer.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sikaflex-410 Asphalt Sealant
August 2021, Version 01.05
020515020000000006

Sikaflex-410AsphaltSealant-en-US-(08-2021)-1-5.pdf

