

## PRODUCT DATA SHEET

# Sikagard® FlexCoat

Two-component, polymer-modified, waterproof, cement-based coating system

### PRODUCT DESCRIPTION

Sikagard® FlexCoat is a polymerized cementitious protective coating. It consists of a unique rubber-like polymer liquid (Part A) mixed at the time of application with a cement aggregate blend (Part B).

### USES

- Balcony deck surfacing
- Concrete exterior restoration
- Sidewalk resurfacing
- Wall refinishing and installation coating
- Stadium renovation
- Swimming pool walkways

### CHARACTERISTICS / ADVANTAGES

- It can be applied over almost any clean, sound surface e.g. concrete, block, masonry, etc. for a number of different floor, wall and roof uses.
- Extraordinary adhesion coupled with its ability to withstand prolonged pedestrian and light vehicular traffic. In these respects, the material is far superior to conventional cementitious coatings.
- Provides a waterproof coating which substantially reduces or prevents water penetration, freeze-thaw scaling and concrete carbonation.
- “Breathable” coating which releases normal entrapped vapor without loosening or blistering.
- Available in natural cement color.
- Sikalastic® Traffic Systems can be top coated with Sikagard® FlexCoat cement based systems. Please refer to the spec component of the Sikalastic®/Sikagard® Flexcoat Hybrid System.

### PRODUCT INFORMATION

<b>Packaging</b>	3.5 gal (13.2 L) unit	55 lb (25 kg) bag
		2.5 gal (9.5 L) liquid
<b>Shelf Life</b>	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging.	
<b>Storage Conditions</b>	Store dry at 40–95 °F (4–35 °C). Protect from freezing. If frozen, discard material.	

## TECHNICAL INFORMATION

<b>Impact Strength</b>	2 lb (0.9 kg) steel ball dropped from 8 ft (2.4 m) height on to coated steel plate	No cracking or detachment	(MIL-D-3134, Para. 4.7.3.)
<b>Compressive Strength</b>	2,440 psi (16.8 MPa)		(ASTM C-109) 75 °F (24 °C) 50 % R.H.
<b>Tensile Strength</b>	430 psi (3.0 MPa)		(ASTM C-190) 75 °F (24 °C) 50 % R.H.
<b>Tensile Adhesion Strength</b>	28 days	515 psi (3.6 MPa)	(ASTM C-882 Type I)*
	* 73 °F (23 °C) and 50 % R.H.		
<b>Reaction to Fire</b>	Complies as Class A Flame Spread - 4 Smoke Density - 0		(UL790) (ASTM E-84 Steiner Tunnel Test)
<b>Behavior after Artificial Weathering</b>	60 cycles	No visible degradation	(ASTM G-23* Weatherometer)
	*(Method 1 at 75 °F (24 °C) and 50 % R.H.)		
<b>Permeability to Water Vapor</b>	1.96 perms/in.		(ASTM E-96)
<b>Diffusion Resistance to Water Vapor</b>	<b>Resistance to Wind-Driven Rain</b> 5" water pressure and 60 gal./hr. water flow	No water or dampness noted on back of test panels	Fed Spec. TT-C-558 (8 hrs.) TT-P-0035 (24 hrs.)
<b>Water Absorption</b>	21 days water immersion 75 °F (24 °C) and 50 % R.H.	< 2 % Weight gain by 4" (101.6 mm) coated concrete cube	
<b>Carbonation Resistance</b>	<b>Hydrocarbon Substances Resistance</b> 21 days repeated reapplication of gasoline	No softening or attack motor oil SAE-10, jet fuel	(ASTM D-1308 Spot Open Test)
<b>Service Temperature</b>	Condition material to 65–75 °F (18–24 °C) before using.		

## SYSTEM INFORMATION

<b>System Structure</b>	Elongation	12%	(ASTM D-412)
	Shore Hardness	Durometer "A" - 82	(ASTM D-2240)

## APPLICATION INFORMATION

<b>Coverage</b>	250 ft <sup>2</sup> /coat/unit (Coverage figures do not include allowance for surface profile and porosity or material waste)		
<b>Layer Thickness</b>	<b>Coat thickness</b>	<b>Number of coat</b>	
	60 mils	2	
<b>Ambient Air Temperature</b>	> 50 °F (10 °C)		

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

- Surface must be clean and sound.
- Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- An open textured surface ICRI CSP-3 is recommended.
- Deeper areas shall be patched with appropriate patch material like SikaQuick® or SikaRepair® products.

### MIXING

- Place the liquid component in appropriate mixing container.
- It is always recommended to start mixing with approximately 80 % of the liquid.
- Add the powder while continuing to mix with a low-speed drill (400–600 rpm) and paddle.
- Mix to a uniform consistency, maximum 3 minutes.

### APPLICATION

- Pre-wet surface to SSD (Saturate Surface Dry).
- Insure good intimate contact with the substrate is achieved.
- Sikagard® FlexCoat can be applied in multiple coats by brush, roller, trowel or spray to a typical thickness of 60 mils (1.5 mm).
- Apply first coat of Sikagard® FlexCoat.
- Apply following coats (one or two depending on service conditions/ requirements) by brush, trowel roller or spray.
- Finish to specified texture.
- Protect newly applied Sikagard® FlexCoat from direct sunlight, wind, rain and freezing.
- Color Finish (optional) – apply Sikagard® FlexCoat ATC acrylic top coat for color finish, when specified, in two coats by roller, brush or spray.

### LIMITATIONS

- Minor shade variation may occur with natural cement color material.
- Not suitable for use in areas where acids or other aggressive chemicals are spilled.
- Top coats strongly recommended for color uniformity.
- Will reflect dynamic concrete cracks.
- Static and dynamic cracks can be detailed in accordance with accepted industry practices of using embedding mesh or other methods to reduce the reflecting of cracks.
- Sikagard® FlexCoat is a dense, cement-based waterproofing material that is vapor permeable. This product will not create a vapor barrier.
- Efflorescence in the existing substrate can result in the failure of the bond or discoloration of the surface if there are areas of concrete that are not protected

from water ingress.

- Sikagard® FlexCoat has been tested with Sikagard® Flexcoat ATC. Use of any other top coat needs to be tested for compatibility and performance.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® 32 Hi-Mod.
- Do not install Sikagard® FlexCoat in cold weather (i.e. below 50 °F/10 °C ) or when rainfall can be expected prior to material setting.
- All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the

obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs.

**NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



**Product Data Sheet**

Sikagard® FlexCoat  
October 2018, Version 01.01  
020302050020000009

SikagardFlexCoat-en-US-(10-2018)-1-1.pdf

