



SODABOND POWER SPRAY

Revision: 01/9/23

Page 1 of 2

Technical Data:

Basis	Synthetic rubber
Curing system	Physical drying
Total solid content	Ca. 14 %
Temperature resistance**	-4°F → 212°F
Evaporation time (=minimum time before bonding)	Ca. 5 min
Open time (73°F, 55% RV)*	Ca. 45 min.
Pressing times	15-30s, press, roll or tap well
Application temperature	41°F → 86°F
Spray pattern	Web
Consumption*	Ca. 300 ml/m ² , each side

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Soudabond Power Spray USA is a ready-to-use, strong and fast contact adhesive based on synthetic rubbers. It is applied two-sided and carried in an aerosol.

Properties

- Universal use
- Complies to Prop. 65
- Complies to CARB VOC
- Short evaporation time
- Fast strength build-up.
- High end strength
- Ready to use and very user-friendly
- Dichloromethane (DCM) free
- Fast drying process.
- Good adhesion to many materials
- Fast hand tight bond.

Applications

- For bonding a broad range of materials
- Suitable for the fast bonding of e.g. plastics, metal, timber, porcelain, cork, leather, ceramics, cardboard, paper and rubber.
- Suitable for bonding of low energy surfaces.

Packaging

Color: transparent

Packaging: 12 Oz. aerosol

Shelf life

At least 18 months in unopened packaging in a cool and dry storage place at temperatures between +41°F and +77°F. Upright storage is recommended. The product should be stored in accordance to the rules of storage of inflammable substances. Consult material safety data sheet for more information.

Substrates

Nature: The materials to be bonded should be flat and well fitting as well as clean, dry and free of dust and grease.

Surface preparation: No pretreatment required.

Rough grinding of smooth surfaces improve the adhesion. Make sure the surface is dry, flat, solid, pure, and free of dust, adhesive residue, fat and oil.

A preliminary adhesion test on every surface is recommended.

Soudabond Power Spray USA can be applied on all substrates. Beware of migration of the plasticizer from soft plastics, this might negatively influence the bond.

Remark: This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.



SOUDABOND POWER SPRAY

Revision: 01/9/23

Page 2 of 2

Application method

Application method: Shake can well before use. When processing keep the aerosol can upright at all times and fully press the nozzle.

Spray at a distance of 2" to 4" from the object. Apply the adhesive evenly to both surfaces to be bonded. Spray the lanes over the surface, preferably having a halfway overlap of the previous lane in order to have covered the whole surface with 2 layers. Two light coats (with overlap) give better results than one thick coat. Wait at least 5 minutes (at 73°F and 50% R.H.) and join the two parts together. Then press firmly together. When making a bond, the applied pressure and not the duration of the compression will determine the ultimate strength. After spraying, hold the can upside down and press the spray head until only propellant and no more product comes out to prevent clogging up of the spray can.

Health- and Safety Recommendations

Take the usual labor hygiene into account. Use only in well-ventilated areas. In case of insufficient ventilation it is appropriate to wear respiratory protection. Consult label and material safety data sheet for more information. Since the can contains flammable propellant, all possible ignition sources should be removed before application.

Remarks

- Do not use in applications where continuous water immersion is possible.
- Not suitable for vinyl or other materials with a high content of plasticizers.
- The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.
- Given the great diversity of possible surfaces, it is recommended to perform an adhesion test on both substrates prior to application.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.