

EXOAIR® AIR BARRIER MEMBRANES

Self-Adhered Air & Vapor Membrane Comparison



MEMBRANE	EXOAIR® 110	EXOAIR® 110AT
Adhesive	SBS Rubberized Asphalt	Butyl
Facer Composition	HDPE (High Density Polyethylene)	HDPP (High Density Polypropolyne)
Facer Color	White with large green logo	White with small green logo & website
Mil Thickness	40 mils	18 mils
Puncture Resistance	49 lbf	52 lbf
Installation Temperature	40°F (4°C) and rising	20°F (-7°C) and rising
In-Service Temperature	Up to 158°F (70°C)	Up to 240°F (116°C)
Weight	68 lbs	39 lbs
Primer Required	Yes, ExoAir Primer	No
UV Exposure	30 days	12 months
NFPA 285 Tested Assembly	No, options with stone wool, please contact Technical Service	Yes, FWFO.EWS0010 & FWFO.EWS0019
Sealants adhere to facer	Dymonic® 100 & Spectrem® 1	Dymonic 100 & Spectrem 1

Tremco | 3735 Green Road | Beachwood, OH 44122 | US: 800.852.9068 | CAN: 800.363.3213 | tremcosealants.com

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



Tremco®, ExoAir®, Dymonic® and Spectrem® are registered trademarks of Tremco Incorporated. Use of the ® symbol indicates registration with the US Patent & Trademark Office and the Canadian Intellectual Property Office.

0324/EA110&110ATCS

tremcocpg.com