
PRODUCT DESCRIPTION

ExoAir® 230 Fluid-Applied Synthetic Permeable Air Barrier Membrane is a monolithic, elastomeric membrane designed to be rolled, sprayed, or troweled onto exterior above-grade wall assemblies to mitigate air infiltration/exfiltration and water penetration while remaining permeable to the passage of water vapor. It may also be used as a liquid-applied flashing, enabling the contractor to address both the membrane and flashing needs with a single material.

BASIC USES

ExoAir 230 is typically applied to exterior sheathing panels, concrete block, poured concrete, wood substrates, Nudura Insulated Concrete Forms (ICF), or insulated concrete forms, as an air and vapor permeable membrane. ExoAir 230 can be used with ExoAir 110, ExoAir 110AT, ExoAir 230 (and mesh) Dymonic® 100 or ExoAir DualFlash® as liquid applied flashing to detail into the rough opening.

FEATURES & BENEFITS

ExoAir 230

- ExoAir 230 is a UV stable, seamless, monolithic membrane that creates a fully adhered air barrier when properly installed.
- The ability to roller, spray, or trowel apply the material affords the contractor the ability to accelerate installation times compared to traditional self-adhered membrane systems.
- The high-performance properties of the ExoAir 230 membrane retard the migration of air and bulk water but allow water vapor to pass through the membrane. As a result, vapor permeable systems like ExoAir 230 allow for more flexibility in the placement of the air barrier membrane in the wall design.
- ExoAir 230 is formulated for UV resistance providing the flexibility to install rainscreen systems with open joints or to allow the membrane to be exposed longer during the construction process.
- ExoAir 230 can be custom colored to meet all of your design needs.
- ExoAir 230 is specifically formulated for design options requiring assemblies that have been evaluated for NFPA 285.
- ExoAir 230 is an approved Water Resistive Barrier when applied to Nudura Insulated Concrete Forms (ICF), or insulated concrete forms.

ExoAir 230LT

- ExoAir 230LT is a low temperature grade of ExoAir 230
- ExoAir 230LT has the same features and benefits as ExoAir 230 listed above

AVAILABILITY

ExoAir 230 is immediately available from your local Tremco Sales Representative or Distributor. For Distributor locations, visit <https://www.tremcosealants.com/>

COVERAGE RATES

Exterior Sheathing or Insulated Concrete Forms: Minimum 48 wet mils (25 dry mils); 33 ft²/gal (3.07 M²/US gal)

Porous Substrates: Minimum 70 wet mils (35 dry mils); 23 ft²/gal (2.13 M²/US gal)

Note: Above listed coverage rates are minimums, installing at a greater thickness is acceptable. For more information, please contact your Tremco Representative

PACKAGING

- 5-gal (19-L) pails
- 52-gal (197-L) drums

COLORS

Standard color: Black & Limestone; Custom colors available upon request.

STORAGE

Store ExoAir 230 in original, undamaged packages in a clean, dry, protected location with temperatures 40 to 100 °F (5 to 37 °C).

SHELF LIFE

1 year when stored in accordance with storage instructions.

APPLICABLE STANDARDS

ExoAir 230 has been tested to the following industry standards for air barriers:

- AATCC 127-2008 Water Resistance: Hydrostatic Pressure Test
- ASTM C1305 Standard Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane
- ASTM D412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension
- ASTM D1970 Standard Specification for Self-Adhering Polymer Modified Bituminous Sheet Materials Used as Steep Roofing Underlayment for Ice Dam Protection
- ASTM D4541 Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
- ASTM E96 Standard Test Methods for Water Vapor Transmission of Materials
- ASTM E331 Standard Test Method for Water Penetration of Exterior Windows, Skylights, Doors, and Curtain Walls by Uniform Static Air Pressure Difference
- ASTM E2178 Standard Test Method for Air Permeance of Building Materials
- ASTM E2357 Standard Test Methods for Determining Air Leakage of Air Barrier Assemblies
- NFPA 285 Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies Containing Combustible Components

FIRE RATED SYSTEMS

ExoAir 230 has been tested in assemblies according to NFPA 285 Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies Containing Combustible Components. All of the NFPA 285 UL listed assemblies using Tremco materials can be found using the technical bulletin: ASHRA 90.1 & NFPA 285: Defining & Specifying to Meet IECC & IBC or utilizing the following link: http://database.ul.com/cgi-bin/XYV/template/LISEXT/1FRAME/showpage.html?name=FWFX.R27656&ccnshorttitle=Exterior+Wall+System+Components&objid=1082999775&cfgid=1073741824&version=versionless&parent_id=1082761881&sequence=1.

For NFPA 285 engineering judgment requests please go to www.tremcosealants.com/NFPA 285 Engineering Judgment Request or contact Tremco Technical Service at 866-209-2404.

LIMITATIONS

- No more than 12 months of UV exposure before façade installation. If membrane is exposed for a period exceeding 12 months, contact Tremco Technical Service for additional recommendations at 866-209-2404, or visit the Technical Resources area of our website at www.tremcosealants.com and "Ask the Expert."

- Do not apply to damp, contaminated or frost-covered surfaces.
- Not to be used as a permanently exposed surface. Contact your local Tremco Sales Representative for project specific requirements.
- Membrane shall be protected from rain and washout prior to drying.
- When applying ExoAir 230 to surfaces below 40 °F (5 °C), please refer to the Technical Bulletin- Cold Temperature Recommendations for Air Barrier Applications at www.tremcosealants.com or contact Tremco Technical Service at 886-209-2404.
- ExoAir 230 is not to be applied directly to fireproofing materials. Contact Tremco Technical Service at www.tremcosealants.com for alternative recommendations.
- Keep product from freezing prior to being applied to the substrate. It is best to store ExoAir 230 off the floor at an ambient temperature above 40 °F (10 °C).

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	DESCRIPTION	
TYPE	Synthetic Acrylic	
COLOR	Limestone; Custom colors available upon request	
SOLIDS	0.53	
APPLICATION	Spray, Roller, or Trowel	
THICKNESS	Exterior Sheathing: Minimum 48 mils (wet), 25 mils (dry); Porous Substrates: Minimum 70 mils (wet), 35 mils (dry)	
STORAGE TEMPERATURE	40 to 100 °F (5 to 37 °C)	
CURE TIME	<u>ExoAir 230</u> : 16 to 24 hr at 75 °F (24 °C), 50% RH <u>ExoAir 230LT</u> : 16 to 24 hr at 20 °F (-6 °C), 50% RH	
APPLICATION TEMPERATURE	<u>ExoAir 230</u> : Above 40 °F (5 °C) and rising. If installing below 40 °F (5 °C), please refer to Cold Weather Air Barrier Installation Technical Bulletin or contact Tremco Technical Service at 866-209-2404. <u>ExoAir 230LT</u> : Above 20 °F (-6 °C) and rising	
SERVICE TEMPERATURE	Intermittent Exposure up to 240 °F (115 °C)	
PROPERTY	TEST METHOD	TYPICAL RESULTS
MAXIMUM V.O.C.	Method 310	ExoAir 230: 18 g/L ExoAir 230LT: 50 g/L
HYDROSTATIC HEAD	AATCC – 127	Pass (5 hours)
CRACK BRIDGING	ASTM C1305	Pass
ELONGATION	ASTM D412 Die C	900%
TENSILE STRENGTH		120 psi
WATER IMMERSION	ASTM D870	Pass

TYPICAL PHYSICAL PROPERTIES

PLIABILITY, 180°, 1" (25 MM) MANDREL	ASTM D1970 – Section 7.6	Pass
(LOW TEMPERATURE FLEX)	ASTM D1970 – Section 7.9	Pass
NAIL SEALABILITY		
ADHESION	ASTM D4541	Concrete: 38 psi Exterior Sheathing: 20 psi
ANTIFUNGAL	ASTM D5590	Pass
FLAME SPREAD	E84	10
SMOKE DEVELOPMENT		25
WATER VAPOR PERMEANCE	ASTM E96 Dry Cup	1.4 US Perms
	ASTM E96 Wet Cup	12.0 US Perms
WATER PENETRATION	ASTM E331	Passed at 15 lb/ft ² (718 Pa); Passed at 6.27 lb/ft ² (300 Pa) for 2 hours
AIR LEAKAGE OF MATERIAL	ASTM E2178; Free Film Method @ 75 Pa	0.00158 cfm/ft ² (0.00805 L/(s•m ²))
	ASTM E2178; Free Film Method @ 300 Pa	0.00435 cfm/ft ² (0.02211 L/(s•m ²))
AIR LEAKAGE OF ASSEMBLY	ASTM E2357	0.003 cfm/ft ² @ 1.56 lb/ft ² (0.013 L/(s•m ²) @ (75 Pa))
FIRE RESISTANCE OF ASSEMBLY	NFPA 285	Pass

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

EX230230LT-DS/0523

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com