

Tremco Incorporated certifies that TREMGard® HB fiber reinforced, elastomeric, acrylic wall coating meets the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TREMGARD HB
Density lb/gal (kg/m)	ASTM D1475	11.0 ± 2.0 lb. (5.0 ± 0.9 kg)
Regulatory VOC	Method 310	21 g/L
Viscosity	ASTM D562	85-141 KU
Solids by Weight	ASTM D1644	63% ± 1%
Solids by Volume	ASTM D2697	52% ± 1%
Accelerated Weathering (1000 hr.)	ASTM D4798	No cracking or checking
Permeance Rating (Wet Cup)	ASTM D1653	12 perms
Tear Resistance	ASTM D624	120-140 lbf/in
Tensile Strength @ 77° F (25° C)	ASTM D2370	375 ± 50 psi
Elongation @ 77° F (25° C)	ASTM D2370	215% ± 25%
Low Temp. Flexibility after 1000 hr. accelerated weathering @ -15° F (-26° C) 1/2" Mandrel	ASTM D522	Passed
Fungus Resistance	ASTM G21	No Growth
Adhesion	ASTM C794/D903	Excellent

* Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical services or your local sales representative for more information.