

# TECHNICAL DATA SHEET

# TREMproof® AMPHIBIA™

Sheet-Applied Waterproofing Membrane

### PRODUCT DESCRIPTION

TREMproof® Amphibia™ Waterproofing Membrane is a self-handling, self-sealing and self-repairing sheet waterproofing membrane. This co-extruded, watertight membrane has three active layers – a watertight EPDM barrier, an active core with the ability to seal when penetrated, and an active barrier which seals the overlap and helps resist lateral movement of water. Also, a non-woven fabric layer promotes the mechanical adhesion of the membrane to the concrete.

#### **BASIC USES**

TREMproof Amphibia Waterproofing Membrane is designed for use over lagging on blindside walls, below grade walls, pile caps, grade beams, under slab, and buried forms such as elevator pits.

## **FEATURES & BENEFITS**

- The membrane's self-handling and self-leveling capabilities reduce the time required for detail work.
- Active layer self-seals overlaps and helps resist water from spreading and provides easy passage of connecting reinforcements.
- Impermeable membrane with no side seepage of water is highly resistant to hydraulic load, and acceptable for use in hydrostatic conditions.
- Non-woven geotextile layer allows for integral adhesion to the reinforced concrete structure.
- Exceptional elongation and crack-bridging characteristics help deliver extreme durability.
- Composition of the membrane allows for longer exposure to weather and construction elements, offering project schedule flexibility.
- Resists aggressive natural ground agents and is usable in the presence of salt water, expanding it's use in a myriad of jobsite conditions.
- Can be applied in cold temperatures to expand time window for installation.
- Compatible with approved Tremco TREMproof®, ExoAir® and TREMDrain® solutions to proved a continuous building envelope.

# **AVAILABILITY**

TREMproof Amphibia Waterproofing Membrane is immediately available from your local Tremco Sales Representative.

#### **PACKAGING**

 $5.91' \times 65.62' (1.8 \text{ M} \times 20 \text{ M}) \text{ rolls } (387.5 \text{ ft}^2), 130 \text{ lbs/roll}, 20 \text{ rolls/pallet}$   $2.95' \times 32.81' (0.9 \text{ M} \times 10 \text{ M}) \text{ rolls } (96.9 \text{ ft}^2), 33 \text{ lbs/roll}, 36 \text{ rolls/pallet}$ 

## **STORAGE**

Store in a dry place protected from UV and humidity, preferably horizontally. Do not double stack pallets.

# **LIMITATIONS**

- Reinforced concrete structures need to be designed to withstand hydrostatic pressures.
- When exposed to temperatures beyone 160 °F (70 °C) TREMproof Amphibia may warp.

# **WARRANTY**

A repair or replacement warranty is available on all Tremco Products. Visit https://www.tremcosealants.com/warranties/ for details.

TYPICAL PHYSICAL PROPERTIE	S	
PROPERTY	DESCRIPTION	
Color	Black	
Installation Temperatures	32 to 95 °F (0 to 35 °C)	
Freeze/Thaw Cycles	No effect before or after installation	
Life Expectancy	Indefinite	
PROPERTY	TEST METHOD	VALUES US
Thickness	ASTM D3767	63 mils/1.6mm
Elongation	ASTM D412	709%
Tensile Strength, film	ASTM D412	927 psi
Peel Adhesion to Concrete	ASTM D903	7 lbs/in.
Nail Sealability	ASTM D1970, sect. 7.9	Passed
Low Temp Flexibility at -20 °F	ASTM D1970, sect. 7.6	Unaffected, Passed
Tear Strength at Break	ASTM D624	161.51 psi
Permeance	ASTM E96 B	0.0685 US Perms
	ASTM E96 BW (Inverted Wet Cup)	0.0158 US Perms
Permeability	ASTM E96 B	0.0048 US Perm-Inch
	ASTM E96 BW	0.0011 US Perm-Inch
Crack Cycling @ -9.4 °F, 100 Cycles	ASTM C836	Unaffected, Pass
Puncture Strength	ASTM E154	156 lbf
Puncture Resistance of	ASTM D4833	52.4 kg/M
Geomembranes		
Hydrostatic Pressure Resistance	ASTM D4068	Pass at 40 hrs.
Resistance to Hydrostatic Head	ASTM D5385	Pass at 231 ft.
Water Absorption	ASTM D570	0.13%

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TPA-BG/0523

-,Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc



