

TECHNICAL DATA SHEET

TREMCO® PUMA BC R

Roller-Grade Polyurethane-Methacrylate (PUMA) Base Coat

PRODUCT DESCRIPTION

Tremco PUMA BC R is a UV-stable, roller-grade base coat material designed to have tenacious adhesion to Tremco PUMA Primer and provide quick turn-around time with cure rates at less than an hour even in the coldest of temperatures. The material will accommodate movement and bridge cracks of up to 1/16" (1.5mm). Tremco PUMA BC R installed over Tremco PUMA Primer can be used as a waterproofing membrane system at terraces, plaza decks, planters, ramps, vertical walls and as a tie-in material directly to hot rubberized asphalt or in flashing applications. Tremco PUMA BC R requires the use of Tremco PUMA Initiator+ for cure.

BASIC USES

Tremco PUMA BC R is commonly used on inclines, vertical transitions, tie-ins and in flashing applications.

AVAILABILITY

Immediately available from your local Tremco Sales Representative.

PACKAGING

Tremco PUMA BC R: 6-gal pails.

INSTALLATION

Tremco PUMA components are designed for use with the Vulkem EWS and TREMproof PUMA systems. Please refer to the appropriate application instructions for complete application details. The techniques involved may require modification due to job-site specific conditions. Consult your Tremco representative for recommended site conditions and requirements.

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
- Use with adequate ventilation.

WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit https://www.tremcosealants.com/warranties/ for details.

TYPICAL PHYSICAL PROPERTIE	ES		
PROPERTY	TEST METHOD	TYPICAL RESULTS	
VOC Content	Method 310	0 g/L	
% Solids (by Weight)	ASTM D1353	100%	
Drying Time @ 75 °F, 50% RH	ASTM D1640	80 mil film, 1 hr	
Elongation	ASTM D638	407%	
Elongation	ASTM D1547	Min 30%	
Tensile Strength	ASTM D638 @ 75 °F	1680 psi	
Tearing Resistance	ASTM D4073	91 lbf	
Hardness (Shore D)	ASTM D2240	35	
Hardness (Shore A)	ASTM D2240	87	
Low-Temperature Crack Bridging	ASTM C1305	Passes	
Taber Abrasion	ASTM C501	Passes	
Peak Load @ 73 °F, avg.	ASTM D1547	>70 lbf/in	
Puncture Resistance	ASTM D5602	>56 lbs	
Water Absorption	ASTM D570	<0.1%	
Water Vapor Transmission	ASTM E96	0.03 perms	
Adhesion-in-Peel	ASTM C794	Concrete failure with primer	
Self-Ignition Temperature	ASTM D1929	800 °F	
Smoke Density	ASTM D2843	4.1%	
Rate of Burn	ASTM D635	1.2 in/min	

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TPBCR-DS/0923

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



