



MasterFormat: 03 39 23

OCTOBER 2024  
(Supersedes January 2022)

# 1150-CLEAR

## Resin-Based, Water Emulsion Concrete Curing Compound

### DESCRIPTION

1150-CLEAR water-based concrete curing compound is formulated from hydrocarbon resins and may be used on interior, exterior, vertical, and horizontal concrete surfaces. Once applied, it forms a liquid membrane that retains an optimum amount of water present in freshly placed concrete to allow complete hydration of the cement. NOTE: After approximately four weeks, the membrane begins to chemically break down. When the curing cycle is complete, the membrane will eventually wear off the surface. This process usually takes another three to five weeks under normal traffic and weathering conditions.

### USES

1150-CLEAR can be used on both interior and exterior applications where paint, resilient tile, or resilient flooring will be applied. Because of the wide variety of paints and adhesives for carpeting and resilient tile in use, contact the manufacturer of the flooring system for application approval on substrates containing residual resin-type curing compounds. A small test application is also recommended.

### FEATURES/BENEFITS

- When properly applied, produces a premium-grade film, which optimizes water retention.
- Furnished as a ready-to-use, true water-based compound.
- Produces hard, dense concrete ... minimizes hair-checking, thermal cracking, dusting, and other defects.
- Enhances the functional capabilities of concrete by "sealing in" the performance assets of strength and long life.
- Offers a compressive strength significantly greater than improperly cured or uncured concrete.
- Increases tensile strength for greater resistance to cracking and surface crazing.

- Improves resistance to the abrasive and corrosive actions of salts and chemicals ... minimizes excessive shrinkage.
- Can be applied quickly and easily with conventional, commercial spray equipment.
- VOC compliant.
- Formulations also available with red fugitive dye added.

### PACKAGING

5 Gallon Pails  
55 Gallon Drums

### COVERAGE

Approximately 200 ft.<sup>2</sup>/gal. Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F, optimum performance and best use is obtained within two years of date of manufacture.

### SPECIFICATIONS/STANDARDS

- ASTM C 309, Type 1, Class A & B (Type 1-D also available)
- AASHTO M 148, Type 1, Class A & B (Type 1-D also available)
- Complies with Arizona Maricopa County, CARB, Colorado AIM, U.S. EPA, OTC Phase I and Phase II, SCAQMD, Utah Department of Air Quality, and all other current North American VOC regulations.
- Tested per CDPH/EHLB Standard Method V1.2-2017 Emission Testing Method (Report available upon request)

### TECHNICAL DATA

VOC Content: 42 g/L

**CONTINUED ON REVERSE SIDE ...**

#### W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

## APPLICATION

**Mixing...** For optimum performance, gentle mixing or agitation is recommended. CAUTION: TO AVOID FOAMING, DO NOT MIX EXCESSIVELY. In the container, 1150-CLEAR appears ivory in color. However, it dries to a clear, transparent coating with a very slight amber tint.

**Application Method...** Application equipment must be clean and free of any previously used materials. Apply in a uniform film to horizontal surfaces as soon as the surface water disappears and the surface will not be marred by walking workmen. On vertical surfaces, apply promptly after the forms are removed. 1150-CLEAR may be applied with a typical commercial hand or power sprayer, such as a Chapin 1949. Use a spray tip that produces a flow of 0.5 GPM under 40 psi (.276 MPa) of pressure.

**Drying Time...** Typically dries in 1 - 2 hours, depending on jobsite conditions (temperature, wind, etc.) Restrict foot traffic for at least four hours. Twelve hours is preferable.

**Cleanup...** Prior to drying, cleanup can be accomplished with soap and water. Once dried, it will be necessary to clean up with mineral spirits or other suitable petroleum distillate.

## PRECAUTIONS

KEEP FROM FREEZING. Do not apply if concrete temperature is less than 40° F. DO NOT MIX WITH COMPOUNDS CONTAINING SOLVENT – SEPARATION WILL OCCUR. DO NOT ADD OR DILUTE WITH ANY OTHER COMPOUND. SURFACE MAY DISCOLOR AND/OR YELLOW DUE TO OVER-APPLICATION. Do not paint or apply resilient flooring over any 1150-CLEAR cured surface without first checking the specifications and securing the approval of the paint or resilient flooring manufacturer.

## HEALTH AND SAFETY

Direct contact may result in mild irritation. Refer to Safety Data Sheet for complete health and safety information.

For most current data sheet, sustainability information, and SDS, visit [www.wrmeadows.com](http://www.wrmeadows.com).



### LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control

over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.